



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 022 261 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
17.07.2002 Bulletin 2002/29

(51) Int Cl.⁷: **C03C 27/12, C08L 29/14,
B32B 17/10**

(21) Application number: **98911011.9**

(86) International application number:
PCT/JP98/01341

(22) Date of filing: **26.03.1998**

(87) International publication number:
WO 99/03793 (28.01.1999 Gazette 1999/04)

(54) INTERLAYER FOR LAMINATED GLASS AND LAMINATED GLASS

ZWISCHENSCHICHT FÜR VERBUNDGLAS UND VERBUNDGLAS

COUCHE INTERMEDIAIRE POUR VERRE FEUILLETE ET VERRE FEUILLETE

(84) Designated Contracting States:
BE DE FR GB IT NL

(30) Priority: **17.07.1997 JP 19247497**
07.08.1997 JP 21328497
20.08.1997 JP 22361397
11.09.1997 JP 24701597
18.09.1997 JP 25321697
06.01.1998 JP 98398
03.02.1998 JP 2213798

(43) Date of publication of application:
26.07.2000 Bulletin 2000/30

(60) Divisional application:
02008486.9

(73) Proprietor: **SEKISUI CHEMICAL CO., LTD.**
Osaka-shi, Osaka 530-8565 (JP)

(72) Inventors:
• **SHICHIRI, Tokushige**
Osaka 565-0841 (JP)
• **MIYAI, Jiro**
Shiga 520-3101 (JP)
• **BANDO, Akihiko**
Minakuchi-cho, Koka-gun, Shiga 528-0056 (JP)
• **TOYAMA, Kiyofumi**
Osaka 569-0031 (JP)
• **AOSHIMA, Yoshio**
Shiga 525-0027 (JP)

• **SANNOMIYA, Isei**
Shiga 520-3333 (JP)
• **NAKAJIMA, Minoru**
Shiga 528-0208 (JP)

(74) Representative: **Hubert, Philippe**
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(56) References cited:
EP-A- 0 373 139 **BE-A- 677 788**
DE-A- 1 926 958 **GB-A- 1 501 977**
JP-A- 60 210 551 **JP-B- 48 005 772**
JP-B- 53 018 207

• **PATENT ABSTRACTS OF JAPAN vol. 015, no.**
115 (P-1181), 19 March 1991 (1991-03-19) & JP 03
005772 A (FUJIXEROX CO LTD), 11 January 1991
(1991-01-11)
• **DATABASE WPI Week 198549, Derwent**
Publications Ltd., London, GB; Class A94, AN
1985-305872 & JP 60 210 551 A (SEKISUI CHEM
IND CO LTD) 23 October 1985

Remarks:

The file contains technical information submitted
after the application was filed and not included in this
specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 022 261 B1

Description

TECHNICAL FIELD

5 [0001] The present invention relates to an interlayer film for laminated glass and to a laminated glass in which said interlayer film for laminated glass is used.

BACKGROUND ART

10 [0002] Laminated glass comprising at least two glass sheets and a plasticized poly(vinyl butyral) interlayer film sandwiched therebetween has fundamental characteristics required of laminated glass. For example, it has good transparency, weather resistance, bond strength, and penetration resistance. It hardly allows its fragments to scatter. Thus, it has so far been widely used as the windshields of automobiles or buildings, for instance.

15 [0003] While laminated glass of this kind is excellent in fundamental characteristics such as mentioned above and in safety, it is poor in moisture resistance. Thus, when the above-mentioned laminated glass is used in a high humidity environment, a problem may arise; namely, the interlayer film in the peripheral region of the laminate may whiten, since the peripheral edges of laminated glass are in direct contact with the environmental air.

[0004] This phenomenon of blushing is associated with the additive used for adjusting the bond strength between the interlayer film and the glass, as mentioned below.

20 [0005] In order that the laminated glass will sufficiently discharge the functions mentioned above, it is necessary to adjust the bond strength between interlayer film and glass so that it may fall within an adequate range. Thus, if the bond strength between interlayer film and glass is too weak, glass fragments formed upon breakage due to an external shock may peel off from the interlayer film and scatter to increase the risk for injuring the human bodies and other objects. If, conversely, the bond strength between interlayer film and glass is excessively high, the glass and interlayer
25 film tend to break simultaneously upon receiving a shock load whereupon glass fragments accompanying fragments of the interlayer film will scatter, thus increasing the risks for injuring the human bodies and other objects.

[0006] On the contrary, when the bond strength between interlayer film and glass is within an adequate range, breakage of glass occurs over a wide area and results in concurrent partial interfacial peeling of the interlayer film and glass from each other and elongation of the interlayer film, and these phenomena are effective in increasing the resistance
30 against shock and penetration.

[0007] Thus, in order to insure that, taking a traffic accident involving an automobile as an example, the shock to the driver and/or passenger may be absorbed, the risk for their being hauled through the broken windshield may be prevented or, in the case of an accident related to a building, the penetration of flying objects against the window pane or scattering of broken glass fragments may be prevented, the bond strength between interlayer film and glass must be
35 judiciously controlled within said suitable range.

[0008] In view of the foregoing, various bond strength control agents for the interlayer film have so far been investigated in order to adjust the bond strength between interlayer film and glass to a level within an adequate range.

40 [0009] Thus, for example, Japanese Kokoku Publication Sho-46-4270 proposes an interlayer film for laminated glass which comprises a poly(vinyl acetal) resin composition containing 0.2 to 0.8% by weight of water and a specific amount of a specific metal alkylcarboxylate as a bond strength control agent. The bond strength between the interlayer film and glass according to the above proposal is adjusted to an adequate range by varying the proportions of the metal alkylcarboxylate distributed in the superficial layer of the interlayer film and in the inside layer of the interlayer film or varying the water content of the interlayer film.

45 [0010] The metal alkylcarboxylate-containing interlayer film such as proposed in the above publication, however, is low in moisture resistance, and the laminated glass manufactured by using said interlayer film has a problem in that when allowed to stand in a high-humidity atmosphere, it tends to undergo severe blushing due to moisture absorption by the interlayer film as the metal alkylcarboxylate content increases since the interlayer film is in direct contact with air in the peripheral region of the laminated glass. The phenomenon of blushing of the interlayer film may be prevented by decreasing the amount of the metal alkylcarboxylate as far as possible or avoiding the use thereof but, in that case,
50 there occurs a problem crucial for the laminated glass that the bond strength between interlayer film and glass exceeds the proper range and is ready to allow simultaneous breakage or penetration of the glass and interlayer film upon receiving to an external shock load or the like.

55 [0011] In Japanese Kokoku Publication Sho-44-32185, there is proposed an interlayer film for laminated glass which comprises a molded poly(vinyl acetal) resin having a water content of 0.1 to 0.8% and containing 0.01 to 3 parts by weight, per 100 parts by weight of the resin, of at least one organic acid selected from among monocarboxylic acids containing 6 to 22 carbon atoms, dicarboxylic acids containing 4 to 12 carbon atoms, aliphatic monoaminomonocarboxylic acids containing 2 to 6 carbon atoms, aliphatic monoaminodicarboxylic acids containing 4 or 5 carbon atoms, citric acid, and mixtures thereof.

[0012] However, this interlayer film has the drawback that the addition of such a carboxylic acid causes the bond strength to change with the lapse of time. Moreover, another problem may arise; the acid may adversely affect the heat resistance and weather resistance of the interlayer film.

[0013] Japanese Kokoku Publication Sho-48-5772 discloses a laminate glass comprising at least two glass sheets glued together by means of a plasticized poly(vinyl acetal) resin composition, said plasticized poly(vinyl acetal) resin composition contains the sodium metal salt of an aliphatic carboxylic acid containing 10 to 22 carbon atoms.

[0014] Furthermore, in Japanese Kokoku Publication Sho-53-18207, the use is proposed of an alkali metal or alkaline earth metal salt of a monocarboxylic or dicarboxylic acid as a bond strength control agent in the plasticized poly(vinyl acetal) resin interlayer film.

[0015] In either of the above two proposals, a metal salt of a carboxylic acid containing a relatively large number of carbon atoms is used as the bond strength control agent, since such salt is readily soluble in the plasticizer contained in the interlayer film.

[0016] However, when a metal salt of a carboxylic acid containing a large number of carbon atoms is used as the bond strength control agent, there occurs a problem that the bond strength between interlayer film and glass changes with the lapse of time. Thus, even when the bond strength is adequate initially, the bond strength will gradually decrease with the lapse of time and the glass will readily undergo peeling when it receives a shock. For preventing this decrease in bond strength, it is necessary to mature the interlayer film by storing the same in an atmosphere of 40 to 50°C for 1 to 2 months, for instance. However, since the interlayer film has tackiness and a tendency toward self-adhesion, it is as a matter of fact difficult to store the interlayer film in such an atmosphere as mentioned above for a long period of time. Even if the maturing is performed, the decrease in bond strength with the lapse of time can be retarded but cannot be made nil, and the problem mentioned above still remains.

[0017] Japanese Kokai Publication Sho-60-210551 discloses a laminated glass comprising at least two glass sheets glued together by means of an interlayer film composed of a plasticized poly(vinyl acetal) resin containing, or carrying as adhered thereto, 0.02 to 0.40 part by weight of the potassium salt of a monocarboxylic acid containing 1 to 6 carbon atoms and 0.01 to 0.26 part by weight of a modified silicone oil per 100 parts by weight of said resin. Certain metal salts, however, may cause blushing of the laminated glass due to their coagulation in the form of particles within the interlayer film. Therefore, from the viewpoint of long-term prevention of blushing resulting from moisture absorption, said laminated glass cannot be said to be a perfect one.

[0018] In Japanese Kokoku Publication Hei-02-41547, there is proposed a poly(vinyl butyral) sheet in which an alkali or alkaline earth metal salt of formic acid is used as the bond strength control agent. Furthermore, in Japanese Kohyo Publication Hei-06-502594, an interlayer film containing potassium acetate added as a bond strength control agent is used in the examples of its specification.

[0019] In the three proposals mentioned above, a metal salt of a carboxylic acid containing a relatively small number of carbon atoms is used to overcome the problems mentioned above in relation to the use of a metal salt of a carboxylic acid containing a large number of carbon atoms.

[0020] When a metal salt of a carboxylic acid containing a small number of carbon atoms is used as the bond strength control agent, the problem of the decrease in bond strength between interlayer film and glass with lapse of time can indeed be solved but the moisture resistance of the interlayer film becomes insufficient and, as a result, another problem arises, namely the peripheral (edge) region of the laminated glass tends to undergo blushing due to absorption of moisture.

[0021] More specifically, the interlayer film is generally capable of absorbing moisture under ordinary atmospheric (humidity) conditions and, therefore, in using it in the manufacture of a laminated glass, it is common practice to submit the interlayer film to the lamination process after adjusting its water content to not more than about 0.5% by weight in an atmosphere of 25% RH, for instance. Since, however, the peripheral region of laminated glass are generally exposed, the interlayer film absorbs moisture in a high-humidity environment, whereby the water content increases to about 2 to 3% by weight. On that occasion, water gathers around minute crystals of said metal salt of a carboxylic acid containing a small number of carbon atoms, such as potassium acetate, magnesium acetate or potassium formate, as occurring in the interlayer film, to cause blushing. If the addition amount of the carboxylic acid containing a small number of carbon atoms or a salt thereof is decreased to prevent blushing, the bond strength between interlayer film and glass will deviate from the proper range, hence the shock absorbing potential, penetration resistance and other properties of the laminated glass will become insufficient.

[0022] In Japanese Kokai Publication Hei-05-186250, an attempt is made to improve the carboxylic acid salt-containing interlayer film in respect of blushing by using an interlayer film for laminated glass which is composed of a resin composition comprising a poly(vinyl acetal) resin, a plasticizer, an alkali or alkaline earth metal salt of a mono- or dicarboxylic acid containing not more than 12 carbon atoms and an organic acid.

[0023] Furthermore, in Japanese Kokai Publication Hei-07-41340, an interlayer film for laminated glass is proposed which is formed from a resin composition comprising a poly(vinyl acetal) resin, a plasticizer, a carboxylic acid metal salt and a straight-chain fatty acid.

[0024] The laminated glass including the interlayer film for laminated glasses according to the above proposals show reduced degrees of blushing in the peripheral region in moisture resistance testing but the extent of reduction in blushing is yet unsatisfactory. Moreover, if the content of the straight-chain fatty acid is increased for further reducing the degree of blushing, foaming and/or discoloration may possibly occur when the laminated glass is exposed to a relatively high temperature.

[0025] While the interlayer films proposed in the above-cited publications are results of attempts to solve the blushing problem by improving the bond strength control agent, those interlayer films which contain no bond strength control agent also whiten as a result of moisture absorption. Our recent research works have revealed that those impurities mentioned below in the resin are involved in the blushing phenomenon as one of the causes thereof.

[0026] The interlayer film for laminated glass of the present invention comprises a poly(vinyl acetal) resin as the main component thereof. The process for producing poly(vinyl acetal) resins comprises a step of neutralization. In this neutralization process, an aqueous solution of sodium hydroxide, sodium hydrogen carbonate or the like sodium salt is used. When the sodium salt is used in excess or when another sodium salt is formed as a result of neutralization, the sodium salt may remain in the product poly(vinyl acetal) resin. This residual sodium salt forms particles during polymerization and/or drying, and those particles promote the aggregation of water on the occasion of water absorption by the poly(vinyl acetal) resin, hence serve as a major cause of blushing of the product interlayer film for laminated glass due to moisture absorption. Furthermore, a sodium salt may remain even in poly(vinyl alcohol) in some instances, and this sodium salt may also serve as a cause of blushing of the interlayer film for laminated glass due to moisture absorption in certain instances.

[0027] In recent years, the trend toward the use of laminated glass as the automobile side glass screen or in buildings has been increasing and, in these applications, laminated glass is often used with the peripheral portions thereof being exposed. The need for preventing the blushing phenomenon is becoming more and more increased.

SUMMARY OF THE INVENTION

[0028] The present invention which solves the above problems has it for its object to provide an interlayer film for laminated glass and a laminated glass in which said interlayer film is used and which shows a much decreased extent of blushing of the peripheral region thereof even when placed in a high-humidity atmosphere, without compromise in those fundamental performance characteristics which are required of laminated glass, such as transparency, weather resistance, adhesion and penetration resistance.

[0029] The present invention consists in an interlayer film for laminated glass comprising a plasticized poly(vinyl acetal) resin and having the haze after 24 hours of immersion of not more than 50% when said interlayer film with a thickness of 0.3 to 0.8 mm is immersed in water at 23°C under the conditions indicated below.

DETAILED DESCRIPTION OF THE INVENTION

[0030] In the following, the present invention is described in detail.

[0031] The interlayer film for laminated glass of the present invention consisting essentially of a plasticized poly(vinyl acetal) resin is such that when said interlayer film with a thickness of 0.3 to 0.8 mm is cut to 4 x 4 cm and immersed in deionized water at 23°C, the haze value after 24 hours of immersion is not more than 50% as measured by using an integrating turbidimeter manufactured by Tokyo Denshoku.

[0032] The inventors of the present invention found that an interlayer film for laminated glass showing a haze of not more than 50% when said interlayer film with a thickness of 0.3 to 0.8 mm is immersed in deionised water at 23°C for 24 hours as indicated above is excellent in moisture resistance, showing little blushing in the peripheral region of the laminated glass even when placed in a high-humidity atmosphere. Based on this finding, the present invention has been completed.

[0033] When the haze mentioned above exceeds 50%, the blushing under high-humidity conditions cannot be fully prevented and poor moisture resistance may result, hence the above range is critical. In the present specification, said haze means a value measured by using an integrating turbidimeter manufactured by Tokyo Denshoku after 24 hours of immersion of a sample interlayer film of 4 x 4 cm with a thickness of 0.3 to 0.8 mm in deionized water at 23°C.

[0034] The interlayer film for laminated glass of the present invention comprises a plasticized poly(vinyl acetal) resin film, and said plasticized poly(vinyl acetal) sheet contains a poly(vinyl acetal) resin as a main component.

[0035] Said poly(vinyl acetal) resin preferably has an average degree of acetalization of 40 to 75 mole percent. When said degree is less than 40 mole percent, the compatibility with the plasticizer will be low, making it difficult; in some instances, to incorporate the plasticizer in an amount necessary for securing penetration resistance. When said degree is over 75 mole percent, the resulting interlayer film for laminated glass will have a low mechanical strength and, in addition, a prolonged reaction time will be required for resin preparation, which is often undesirable from the process viewpoint. A more preferred range is 60 to 75 mole percent. When said degree is less than 60 mole percent, the

hygroscopicity will be high and, therefore, blushing may readily occur in some instances. A still more preferred range is 64 to 71 mole percent.

[0036] In the above plasticized poly(vinyl acetal) resin, the vinyl acetate content is preferably not more than 30 mole percent. When it is over 30 mole percent, blocking will readily occur in the process of resin production, making the resin production difficult. It is preferred that said content be not more than 19 mole percent.

[0037] Said plasticized poly(vinyl acetal) resin comprises a vinyl acetal component, a vinyl alcohol component and a vinyl acetate component. These components can be quantitated according to JIS K 6728 "Methods of testing poly(vinyl butyral)" or by the nuclear magnetic resonance (NMR) method, for instance.

[0038] In cases where the poly(vinyl acetal) resin comprises other than a poly(vinyl butyral) resin, the vinyl alcohol component and vinyl acetate component are first quantitated. The amount of the remaining vinyl acetal component can then be calculated by subtracting the amounts of the above both components from 100.

[0039] The poly(vinyl acetal) resin mentioned above can be produced by per se known methods. Thus, for example, poly(vinyl alcohol) is dissolved in warm water and, while maintaining the resulting aqueous solution at a specific temperature, for example 0 to 95°C, preferably 10 to 20°C, a necessary acid catalyst and a necessary aldehyde are added, and the acetalization reaction is allowed to proceed with stirring. The reaction temperature is then raised to 70°C for carrying the reaction to completion, followed by neutralization, washing with water and drying, to give a poly(vinyl acetal) resin powder.

[0040] The above poly(vinyl alcohol) to serve as the starting material preferably has an average degree of polymerization of 500 to 5,000, more preferably 1,000 to 2,500. When it is less than 500, the product laminated glass may have only a low penetration resistance. When it exceeds 5,000, resin film forming may become difficult and, in addition, the strength of the resin film may become excessively high.

[0041] It is preferred that the vinyl acetate component in the poly(vinyl acetal) resin obtained account for not more than 30 mole percent. Therefore, it is preferred that the degree of saponification of the above poly(vinyl alcohol) be not less than 70 mole percent. When said degree is less than 70 mole percent, the transparency and/or heat resistance of the resin may be low and the reactivity may also be low. More preferably, said degree is not less than 95 mole percent.

[0042] The average polymerization degree and saponification degree of the poly(vinyl alcohol) can be determined according to JIS K 6726 "Methods of testing poly(vinyl alcohol)", for instance.

[0043] The aldehyde mentioned above is preferably an aldehyde containing 3 to 10 carbon atoms. When the number of carbon atoms is less than 3, sufficient resin film moldability may not be obtained in some instances. When it exceeds 10, the reactivity for acetalization will be low and, in addition, resin blocking may readily occur and cause difficulties in resin synthesis.

[0044] The aldehyde mentioned above is not limited to any particular species but includes aliphatic, aromatic, alicyclic and other aldehydes, such as propionaldehyde, n-butyraldehyde, isobutyraldehyde, valeraldehyde, n-hexylaldehyde, 2-ethylbutyraldehyde, n-heptylaldehyde, n-octylaldehyde, n-nonylaldehyde, n-decylaldehyde, benzaldehyde and cinnamaldehyde. Preferred are aldehydes containing 4 to 8 carbon atoms, such as n-butyraldehyde, n-hexylaldehyde, 2-ethylbutyraldehyde and n-octylaldehyde. Among them, n-butyraldehyde, which contains 4 carbon atoms, is more preferred, since the use of the resulting poly(vinyl acetal) resin contributes to an increased bond strength of the resin film as well as excellent weather resistance and to: easy production of the resin. The aldehydes may be used either singly or in a combination of two or more species.

[0045] In the interlayer film of the present invention, the particle diameter of a sodium salt therein is preferably not more than 5 µm. The particle diameter of potassium salt in the interlayer film is preferably not more than 5 µm.

[0046] When the sodium salt has a particle diameter greater than 5 µm or the potassium salt has a particle diameter greater than 5 µm, the salt particles may promote water aggregation and become a primary cause of blushing of the obtained interlayer film due to moisture absorption.

[0047] The sodium salt or potassium salt particle diameter referred to above is the particle diameter in the interlayer film. While the particle diameters of the sodium salt and potassium salt in the poly(vinyl acetal) resin, which are the primary raw material, are decreased in the process of sheet forming in some instances, said particle diameters are retained in other instances. Therefore, it is preferred that the particle diameters of sodium salt and potassium salt in the poly(vinyl acetal) resin be also within the above-specified range.

[0048] The particle diameters of sodium salt and potassium salt in the interlayer film can be determined by secondary ion imaging using a time-of-flight secondary ion mass spectrometer (TOF-SIMS).

[0049] In the interlayer film of the present invention, the sodium concentration is preferably not more than 50 ppm, and the potassium concentration in the interlayer film is preferably not more than 100 ppm. More preferably, the sodium concentration should be not less than 0.5 ppm and not more than 15 ppm, and the potassium concentration should be not less than 0.5 ppm and not more than 100 ppm.

[0050] When the sodium content of the interlayer film is over 50 ppm and/or the potassium content is over 100 ppm, water molecules gather around the sodium element and potassium element and grow to macroscopic sizes, whereupon blushing may become prominent. To prepare an interlayer film having a sodium content of less than 0.5 ppm and a

potassium content of less than 0.5 ppm is not preferred from practical points of view in some instances, since the step of washing for eliminating the remaining sodium element or potassium element coming from the resin preparation step must be excessively prolonged and/or the degree of purification of water and other raw materials must be raised, among other measures, hence much time and expenses are required.

[0051] The concentration of sodium and that of potassium in the interlayer film can be determined by elemental analysis using an ICP emission spectrometer. The elemental analysis by ICP emission spectrometry is a technique comprising heating and decomposing the sample with sulfuric acid and nitric acid, making the decomposition product to volume with ultrapure water and then performing assaying by the ICP-AES method.

[0052] The inclusion of said sodium and/or potassium results from the use, for example in the preparation of poly(vinyl acetal) resin, of a sodium or potassium element-containing neutralizing agent, such as sodium carbonate, sodium hydrogen carbonate, sodium acetate, sodium hydroxide, potassium carbonate, potassium hydrogen carbonate, potassium acetate or potassium hydroxide, for neutralization of the acid catalyst used for the reaction, such as sulfuric acid or hydrochloric acid.

[0053] The neutralization procedure in the above poly(vinyl acetal) resin production process is effective in preventing the acid catalyst such as hydrochloric acid (HCl), which is essential for the poly(vinyl acetal) resin formation reaction in the preceding step, from remaining in the resin and deteriorate the very resin.

[0054] Usable as said neutralizing agent are alkali metal salts and alkaline earth metal salts. Unlike alkali metals, alkaline earth metals, when remaining in the interlayer film in fairly large amounts, can prevent blushing under high-humidity conditions, hence are preferred.

[0055] As said alkaline earth metal salts, there may be mentioned, among others, magnesium salts such as magnesium hydrogencarbonate, magnesium hydroxide, basic magnesium carbonate, barium salts such as barium hydroxide, and calcium salts such as calcium hydroxide.

[0056] The inclusion of said sodium and/or potassium also results from the sodium or potassium salt of a carboxylic acid and octylic acid, etc., added as a bond strength control agent, which is remaining in the interlayer film, or from the sodium element or potassium element contained in water and other raw materials used, in particular in poly(vinyl alcohol), and remaining in the interlayer film.

[0057] The amount of such alkali metals contained in pure water can be reduced to 1 ppm or less through the use of deionized water, for instance. On the other hand, the alkali metal content of the poly(vinyl alcohol) comes from the sodium acetate formed in the course of saponification of poly(vinyl acetate) in the process for producing the raw material poly(vinyl alcohol), and it is generally 0.4 to 1.5% by weight.


[0058] Therefore, by using a poly(vinyl alcohol) material having a sodium acetate content of not more than 0.4% by weight, the sodium element in the resin, which is hardly removable by washing, can be reduced and, by intensified washing or like measures, the sodium element can be consistently reduced to 50 ppm or below.

[0059] In the above process for poly(vinyl acetal) resin production, it is also possible to reduce the alkali metal content by washing the poly(vinyl acetal) resin with water until a pH of 5 or above is attained, followed by drying at a temperature not higher than 60°C, without resort to the neutralization procedure mentioned above. By sufficient washing with water until a pH of 5 or above is attained, the content of the alkali metal, which is causative of blushing of the resulting resin film, can be reduced to a amount not over a required amount. Further, by drying at a relatively low temperature not higher than 60°C, the resin can be protected against deterioration due to the inclusion of alkali metal and the remaining acid catalyst and, at the same time, the drying equipment can be protected from being corroded by the acid. Although the drying procedure may be carried out by any ordinary method, the vacuum drying method, in particular, is efficient and superior.

[0060] In the above step of washing with water, washing is preferably carried out with water at a temperature of not lower than 40°C. Taking into consideration the fact that the resin in the slurry swells at 40°C or above, the temperature of water to be used for washing is raised to 40°C or above so that the efficiency of washing can be improved and resin deterioration due to the inclusion of alkali metal and/or acid catalyst residues can be prevented. By using washing water at 40°C or above, preferably 40 to 60°C, in the step of washing, the resin in the slurry swells and the acid (HCl) and the neutralization product (alkali metal-containing product) contained in the resin can be readily washed away, whereby the washing efficiency can be improved. If the washing water temperature is below 40°C, the resin cannot swell to a satisfactory extent, hence the efficiency can hardly be improved. If the washing water temperature is higher than 60°C, the resin softens and resin particles stick together, forming blocks, hence the resin cannot have a stable particle size; in addition, any marked improvement in efficiency cannot be expected as compared with water at 60°C and, thus, a waste of energy results.

[0061] An alternative method may also be mentioned for preventing the above-mentioned inclusion of sodium and potassium. This method comprises using, in synthesizing a poly(vinyl acetal) resin by reacting poly(vinyl alcohol) with an aldehyde in the presence of hydrochloric acid catalyst, an epoxide as both a reaction terminator and a hydrochloric acid eliminator and subjecting the resulting poly(vinyl acetal) resin to sheet formation.

[0062] Said epoxide includes, among others, 1,2-epoxides of the general formula (I):



(wherein R¹ and R² each represents a hydrogen atom or an alkyl group and n represents an integer of 0 to 3), as well as 1,3-epoxides such as trimethylene oxide, tetrahydrofuran and tetrahydropyran, 1,4-epoxides, 1,5-epoxides. These may be used singly or two or more of them may be used combinedly. Particularly preferred as the epoxide are ethylene oxide, propylene oxide.

[0063] The above epoxide can be used in an effective amount sufficient to terminate the reaction and eliminate the hydrochloric acid.

[0064] As regards the mode of use of the above epoxide, the epoxide is used in lieu of the hydrochloric acid catalyst neutralizing agent to terminate the acetalization reaction and further to eliminate the hydrochloric acid, whereby the resin can be prevented from deterioration due to the inclusion of alkali metal and/or retention of acid catalyst.

[0065] In the present invention, it is preferred that a dispersant be incorporated in the interlayer film for laminated glass so that blushing under high-humidity conditions can be prevented more effectively.

[0066] As said dispersant, there may be mentioned compounds capable of forming complexes with sodium salts and potassium salts, organic acids compatible with the resin and plasticizer, and amines compatible with the resin and plasticizer.


[0067] Said compounds capable of forming complexes with sodium salts and potassium salts render the surroundings of metal salts such as sodium salts and potassium salts hydrophobic and thereby render it difficult for water to approach said surroundings, with the result that even upon moisture absorption by the poly(vinyl acetal) resin, the interlayer film for laminated glass as obtained can be prevented from undergoing blushing.

[0068] The above-mentioned compound capable of forming complexes with sodium salts and potassium salts includes but is not limited to ethylenediaminetetraacetic acid, salicylaldehyde, salicylic acid, salicylanilide, oxalic acid, 1,10-phenanthroline, acetylacetone, 8-hydroxyquinoline, dimethylglyoxime, 1,1-cyclohexanediacetic acid, salicylaldoxime and glycine. These may be used either singly or two or more of them may be used in combination.

[0069] The addition amount of the compound capable of forming complexes with sodium salts and potassium salts depends on the amount of the metal salt remaining in the poly(vinyl acetal) resin but is preferably within the range of 0.02 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount below 0.02 part by weight, the preventive effect on the blushing due to moisture absorption may be insufficient. At an addition amount exceeding 2 parts by weight, the compatibility with the poly(vinyl acetal) resin will be poor and a transparency problem may arise in some instances. A more preferred range is 0.05 to 1 part by weight.

[0070] Organic acids compatible with the resin and plasticizer and amines compatible with the resin and plasticizer can also be used as the dispersant mentioned above.

[0071] Among said organic acids compatible with the resin and plasticizer, at least one member selected from the group consisting of sulfonic acids containing 2 to 21 carbon atoms, carboxylic acids containing 2 to 20 carbon atoms, and phosphoric acids of the general formula (II) given below is used.



(In the above formula, R³ represents an aliphatic hydrocarbon group containing 1 to 18 carbon atoms or an aromatic hydrocarbon group containing 1 to 18 carbon atoms, and R⁴ represents a hydrogen atom, an aliphatic hydrocarbon group containing 1 to 18 carbon atoms, or an aromatic hydrocarbon group containing 1 to 18 carbon atoms.)

[0072] Referring to the sulfonic acids containing 2 to 21 carbon atoms, if the number of carbon atoms is less than 2, the hydrophilicity will be high, hence the compatibility with the poly(vinyl acetal) resin will be poor and insufficient dispersion will result. If the number of carbon atoms is over 21, the sulfonic acid will be hydrophobic, hence the com-

patibility with the poly(vinyl acetal) resin will be poor and phase separation may possibly occur. More preferred are those containing 7 to 18 carbon atoms.

[0073] The sulfonic acids containing 2 to 21 carbon atoms may be aliphatic or aromatic, for instance. The sulfonic acids containing 2 to 21 carbon atoms thus include, but are not limited to, benzenesulfonic acid, naphthalenesulfonic acid, alkylsulfonic acids with the alkyl moiety thereof containing 2 to 21 carbon atoms, alkylbenzenesulfonic acids with the alkyl moiety thereof containing 2 to 15 carbon atoms, and alkyl naphthalenesulfonic acids with the alkyl moiety thereof containing 2 to 11 carbon atoms, among others. More specifically, there may be mentioned p-toluenesulfonic acid, dodecylbenzenesulfonic acid, camphorsulfonic acid, hydroxypropanesulfonic acid, mesitylenesulfonic acid, and the like. These may be used singly or two or more of them may be used in combination.

[0074] The addition amount of the sulfonic acids containing 2 to 21 carbon atoms is preferably 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount less than 0.01 part by weight, the preventive effect on the blushing due to moisture absorption will be insufficient in some instances. At an addition amount exceeding 2 parts by weight, the resin deterioration may be promoted or the sulfonic acids themselves may cause the blushing. A more preferred addition amount is within the range of 0.03 to 1 part by weight.

[0075] Referring to the carboxylic acids containing 2 to 20 carbon atoms, if the number of carbon atoms is less than 2, the hydrophilicity will be high, hence the compatibility with the poly(vinyl acetal) resin will be poor and insufficient dispersion will result. If the number of carbon atoms is over 20, the carboxylic acid will be hydrophobic, hence the compatibility with the poly(vinyl acetal) resin will be poor and phase separation may possibly occur. More preferred are those containing 6 to 14 carbon atoms.

[0076] The carboxylic acids containing 2 to 20 carbon atoms may be aliphatic or aromatic, for instance. They may be dicarboxylic acids. Said carboxylic acids containing 2 to 20 carbons atoms thus include, but are not limited to, acetic acid, propionic acid, butyric acid, isobutyric acid, 2-ethylbutyric acid, octanoic acid, 2-ethylhexylic acid, lauric acid, myristic acid, stearic acid, oxalic acid, malonic acid, succinic acid, adipic acid, pimelic acid, sebacic acid, oleic acid, benzoic acid, tolucic acid, naphthoic acid, 1,1-cyclohexanediadic acid, salicylic acid. These may be used singly or two or more of them may be used in combination.


[0077] The addition amount of the carboxylic acids containing 2 to 20 carbon atoms is preferably 0.01 to 3 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount less than 0.01 part by weight, the preventive effect on the blushing due to moisture absorption will be insufficient in some instances. At an amount exceeding 3 parts by weight, the compatibility with the resin will be poor and a transparency problem may arise or resin deterioration may be promoted. A more preferred range is 0.05 to 1 part by weight.

[0078] Referring to R³ and R⁴ in the phosphoric acids represented by the above general formula (II), if the number of carbon atoms in the aliphatic hydrocarbon group or aromatic hydrocarbon group exceeds 18, the phosphoric acid will be hydrophobic, hence the compatibility with the poly(vinyl acetal) resin will be poor. A more preferred range of the number of carbon atoms is 6 to 12.

[0079] The phosphoric acids of general formula (II) include but are not limited to methylphosphoric acid, ethylphosphoric acid, propylphosphoric acid, isopropylphosphoric acid, butylphosphoric acid, laurylphosphoric acid, stearylphosphoric acid, 2-ethylhexylphosphoric acid, di(2-ethylhexyl)phosphoric acid, isodecylphosphoric acid, phenylphosphoric acid, dimethylphosphoric acid, diethylphosphoric acid, diisopropylphosphoric acid, dioctylphosphoric acid, diphenylphosphoric acid and dibenzylphosphoric acid. These may be used singly or two or more of them may be used in combination.

[0080] The addition amount of the phosphoric acid of general formula (II) is preferably 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount below 0.01 part by weight, the preventive effect on the blushing due to moisture absorption will be insufficient in some instances. At an amount exceeding 2 parts by weight, resin deterioration may be rather promoted or the phosphoric acid itself may cause the blushing. A more preferred range is 0.03 to 1 part by weight.

[0081] The organic acid compatible with the resin and plasticizer is used in combination with the amine compatible with the resin and plasticizer. Suited for use as the amine compatible with the resin and plasticizer are amines of the general formula (III):



(wherein R⁵, R⁶ and R⁷ may be the same or different and each represents a hydrogen atom, an aliphatic hydrocarbon group containing 1 to 20 carbon atoms or an aromatic hydrocarbon group containing 1 to 20 carbon atoms).

[0082] When the number of carbon atoms in the aliphatic hydrocarbon group or aromatic hydrocarbon group mentioned above exceeds 20, the amine becomes hydrophobic, hence the compatibility with the poly(vinyl acetal) resin may be poor in some instances. It is preferred that one of R⁵, R⁶ and R⁷ be a long-chain one. More preferably, R⁵ and R⁶ each independently is a hydrogen atom or a hydrocarbon group containing 1 or 2 carbon atoms, and R⁷ is a hydrocarbon group containing 6 to 16 carbon atoms.

[0083] The amine of general formula (III) includes but is not limited to primary amines such as methylamine, ethylamine, propylamine, hexylamine, octylamine, decylamine, dodecylamine, tetradecylamine, aniline, toluidine, naphthylamine; secondary amines such as dimethylamine, diethylamine, dipropylamine, dihexylamine, dioctylamine, N-methylaniline; tertiary amines such as trimethylamine, triethylamine, N,N-dimethylhexylamine, N,N-dimethyloctylamine, N,N-dimethyldodecylamine, N,N-dimethyldodecylamine, N,N-dimethylaniline, pyridine. These may be used singly or two or more of them may be used in combination.

[0084] When a sulfonic acid containing 2 to 21 carbon atoms is used as the organic acid compatible with the resin and plasticizer, the addition amount of the amine of general formula (III) is preferably 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount less than 0.01 part by weight, the preventive effect on the blushing due to moisture absorption may be insufficient. At an addition amount exceeding 2 parts by weight, the compatibility with the resin will be poor, and a transparency problem may arise or the interlayer film may be discolored. A more preferred range is 0.02 to 1 part by weight.

[0085] When a carboxylic acid containing 2 to 20 carbon atoms is used as the organic acid compatible with the resin and plasticizer, the addition amount of the amine of general formula (III) is preferably 0.01 to 3 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount below 0.01 part by weight, the preventive effect on the blushing due to moisture absorption may be insufficient. At an addition amount exceeding 3 parts by weight, the compatibility with the resin will be poor, and a transparency problem may arise or the interlayer film may be discolored. A more preferred range is 0.05 to 1 part by weight.

[0086] When a phosphoric acid of the above general formula (II) is used as the organic acid compatible with the resin and plasticizer, the addition amount of the amine of general formula (III) is preferably 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount below 0.01 part by weight, the preventive effect on the blushing due to moisture absorption may be insufficient. At an addition amount exceeding 2 parts by weight, the compatibility with the resin will be poor, and a transparency problem may arise or the interlayer film may be discolored. A more preferred range is 0.05 to 1 part by weight.

[0087] The organic acid compatible with the resin and plasticizer and the amine compatible with the resin and plasticizer used as a dispersant as mentioned above respectively take the form of ions, for example sulfonyl ion, carboxyl ion, phosphoryl ion, and ammonium ion. These ions act on the surface of the particulate metal salt in the poly(vinyl acetal) resin and bind the metal ion and counter ion constituting said metal salt. When the resin is kneaded prior to sheet formation, the metal salt carrying these ions are dispersed in the resin and, as a result, the metal salt in particulate form becomes smaller or disappear. Therefore, local aggregation of water molecules is prevented and, even when the poly(vinyl acetal) resin absorbs moisture, the interlayer film of the laminated glass can be prevented from blushing.

[0088] In the present invention, it is preferred that the interlayer film for laminated glass contain at least one salt selected from the group consisting of alkali metal salts and alkaline earth metal salts as a bond strength control agent.

[0089] Said alkali metal salts and alkaline earth metal salts include but are not limited to potassium salts, sodium salts, magnesium salts and so forth. As the salt-forming acid, there may be mentioned organic acids, for example carboxylic acids such as octylic acid, hexylic acid, butyric acid, acetic acid and formic acid; and inorganic acids such as hydrochloric acid and nitric acid.

[0090] Among the alkali metal salts and alkaline earth metal salts mentioned above, alkali metal salts of organic acids containing 5 to 16 carbon atoms and alkaline earth metal salts of organic acids containing 5 to 16 carbon atoms are preferred. More preferred are the magnesium salts of carboxylic acids or dicarboxylic acids containing 6 to 10 carbon atoms.

[0091] Said magnesium salts of carboxylic acids or dicarboxylic acids include but are not limited to magnesium 2-ethylbutyrate, magnesium valerate, magnesium hexanoate, magnesium heptanoate, magnesium octanoate, magnesium nonanoate, magnesium decanoate, magnesium glutarate and magnesium adipate.

[0092] It is supposed that the magnesium salts of carboxylic acids or dicarboxylic acids containing 6 to 10 carbon atoms occur in the form of salts in the sheet without electrolytic dissociation, and attract water molecules, making it possible to suppress the bond strength between the interlayer film and glass, with the result that the penetration resistance of the product laminated glass can be improved. Furthermore, since they are distributed in high concentrations on the sheet surface without aggregation in the sheet, they show a bond strength modifying effect even in small amounts, without causing excessive blushing upon moisture absorption, therefore they are preferable.

[0093] Said alkali metal salts and alkaline earth metal salts preferably have a particle diameter of not more than 3

μm , more preferably not more than $1\ \mu\text{m}$. When said diameter exceeds $3\ \mu\text{m}$, water molecules around the alkali metal salt and/or alkaline earth metal salt particles grow to a macroscopic size, with the result that the blushing becomes unfavorably remarkable in some instances.

[0094] The means for reducing the particle size of $3\ \mu\text{m}$ or less is not limited to any particular method. Thus, for example, there may be mentioned the method comprising using a compound readily soluble in the poly(vinyl acetal) resin and plasticizer as a bond strength control agent, the method comprising using a compound which is hardly soluble in the poly(vinyl acetal) resin and plasticizer but hardly aggregate in the poly(vinyl acetal) resin and plasticizer, and the method comprising combinedly using a dispersant or compatibilizing agent capable of dispersing said compounds.

[0095] When a poly(vinyl butyral) resin is used as the poly(vinyl acetal) resin and triethylene glycol 2-ethylbutyrate is used as the plasticizer, the compound readily soluble in the above formulation is, for example, an organic acid salt, such as magnesium octanoate, magnesium neodecanoate and magnesium adipate. These are suitably used either singly or in a combination of two or more species.

[0096] As the compound hardly soluble in the above formulation but hardly aggregating in the formulation, there may be mentioned inorganic acid magnesium salts such as magnesium chloride and magnesium nitrate. These are suitably used either singly or in a combination of two or more species. The dispersant or compatibilizing agent capable of dispersing the compound hardly soluble in the formulation is not limited to any particular species but includes alcohols such as ethanol and octyl alcohol, and long-chain organic acids such as octanoic acid and nonanoic acid, among others. These are suitably used either singly or in a combination of two or more species.

[0097] Among the various methods mentioned above, the method comprising using a compound which is by itself readily soluble in the poly(vinyl acetal) resin and plasticizer is most preferred. The method comprising using a compound hardly aggregating in the poly(vinyl acetal) resin and plasticizer is next preferred.

[0098] When a diester compound is used as the plasticizer, it is preferred that the alkali metal salt and alkaline earth metal salt mentioned above have the same acid component structure as that of the diester compound. Owing to their having an acid component structure identical or similar to that of the diester compound used as the plasticizer, they can be present stably and uniformly dispersed in the sheet, hence will not undergo changes with the lapse of time.

[0099] When triethylene glycol di-2-ethylbutyrate (hereinafter referred to sometimes as "3GH") or dihexyl adipate (hereinafter referred to sometimes as "DHA") is used as the plasticizer, a metal salt of a carboxylic acid containing 5 or 6 carbon atoms is preferably used as a bond strength control agent, since, in that case, the decrease in the bond strength with the lapse of time between the interlayer film and glass can be prevented and the prevention of blushing and prevention of the decrease in the bond strength with the lapse of time can be simultaneously accomplished. When triethylene glycol di-2-ethylhexanoate (hereinafter referred to sometimes as "3GO") is used as the plasticizer, it is preferred, for the same reasons, that a metal salt of a carboxylic acid containing 6 to 8 carbon atoms be contained in the formulation. When tetraethylene glycol di-2-ethylhexanoate (hereinafter referred to sometimes as "4GO") is used as the plasticizer, it is preferred that a metal salt of a carboxylic acid containing 6 or 7 carbon atoms be contained in the formulation.

[0100] For preventing the above plasticized poly(vinyl acetal) resin as far as possible from undergoing heat-induced hydrolysis in the sheet forming step, the use of plasticizers less susceptible to hydrolysis such as plasticizers of the side chain type, such as 3GH, 3GO and 4GO, or of the adipate type, such as DHA, is preferred to the use of such plasticizers as triethylene glycol diheptanoate (3G7) and tetraethylene glycol diheptanoate (4G7).

[0101] Said 3GH has long been in use as a plasticizer in interlayer films with practically acceptable results and the organic acid constituent thereof is of the side chain type. Therefore, 3GH is more advantageous than 3G7, 4G7 and the like, which are of the straight chain type, in that it is less hydrolyzable. The above-mentioned 3GO and 4GO are advantageous in that they are higher in boiling point than 3GH, for instance, and therefore are less volatile in the sheet forming step or in the lamination step.

[0102] Said 3GH, 3GO, 4GO and DHA may be used singly or in combination with another plasticizer such as mentioned hereinafter. The mixing ratio of said 3GH, 3GO, 4GO and/or DHA to said other plasticizer is preferred that the amount of said other plasticizer be less than 50% by weight of the amount of said plasticizer(s) 3GH, 3GO, 4GO and DHA. When this ratio is over 50% by weight, the characteristic features of 3GH, 3GO, 4GO and DHA are sacrificed by said other plasticizer and, therefore, the effect of the bond strength control agent used in combination with them may not be expressed to a satisfactory extent.

[0103] The carboxylic acid metal salt to be used as the bond strength control agent, when the plasticizer in the interlayer film is specified as mentioned above, includes but is not limited to pentanoic acid (of 5 carbon atoms) metal salts, hexanoic acid (2-ethylbutanoic acid) (of 6 carbon atoms) metal salts, heptanoic acid (of 7 carbon atoms) metal salts, octanoic acid (of 8 carbon atoms) metal salts, and so forth. According to the plasticizer mentioned above, one, two or more of these are suitably used. The carboxylic acid may be of the straight chain type or of the side chain type.

[0104] When a metal salt of a carboxylic acid containing too small a number of carbon atoms is used, the interlayer film obtained will have an insufficient moisture resistance, which may allow the blushing phenomenon to occur widely. Conversely, if a metal salt of a carboxylic acid containing an excessively large number of carbon atoms is used, the

decrease in the bond strength with the lapse of time between the interlayer film and glass may be insufficient.

[0105] The above-mentioned carboxylic acid metal salt as the bond strength control agent may be used independently or in combination with another bond strength control agent, for example a bond strength control agent of metal salt of carboxylic acid containing 1 to 4 carbon atoms type such as magnesium formate, magnesium acetate, magnesium propanoate or magnesium butanoate, or a modified silicone oil bond strength control agent such as mentioned later herein.

[0106] When said alkali metal salt and/or alkaline earth metal salt is added as a bond strength control agent, the addition amount thereof is preferably 0.01 to 0.2 part by weight per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount lower than 0.01 part by weight, the bond strength modifying effect will be nil, hence the penetration resistance of the product laminated glass may be low. At an amount exceeding 0.2 part by weight, the control agent may bleed out, impairing the transparency of the product laminated glass and at the same time leading to an excessively decreased bond strength between interlayer film and glass. A more preferred range is 0.03 to 0.08 part by weight.

[0107] When the alkali metal salt is a sodium salt, blushing tends to occur very readily, so that the sodium concentration should preferably be not more than 50 ppm. When the alkali metal salt is a potassium salt, too, blushing may occur readily, hence the potassium concentration should preferably be not more than 100 ppm.

[0108] In addition to the cases where said alkali metal salt and/or alkaline earth metal salt is added as the bond strength control agent, as mentioned above, there are cases where said salts come from the alkali metal salt or alkaline earth metal salt used as a neutralizing agent for the acid catalyst such as sulfuric acid or hydrochloric acid, used in the reaction for producing poly(vinyl acetal) resin, or cases in which said salt comes from one or more of various raw materials and water used in the reaction for producing poly(vinyl acetal) resin which contains said salt. The alkali metal salt and alkaline earth metal salt as said neutralizing agent may be used also as the bond strength control agent.

[0109] The interlayer film for laminated glass of the present invention comprises a plastic resin film composed of the above-mentioned poly(vinyl acetal) resin, a plasticizer and, where necessary, an additive such as the above-mentioned dispersant and/or bond strength control agent.

[0110] The plasticizer to be used in the present invention includes those known plasticizers for use in interlayer films of this kind, for example organic ester type plasticizers such as monobasic acid esters and polybasic acid esters, and phosphorus type plasticizers such as organic phosphate and organic phosphite plasticizers.

[0111] Preferred among said monobasic acid esters are those glycol esters which can be obtained by the reaction of triethylene glycol with an organic acid such as butyric acid, isobutyric acid, caproic acid, 2-ethylbutyric acid, heptanoic acid, n-octylic acid, 2-ethylhexylic acid, pelargonic acid (n-nonylic acid) or decylic acid. In addition, esters of tetraethylene glycol or tripropylene glycol with the organic acids mentioned above may also be used.

[0112] Preferred as said polybasic acid esters are, for example, esters of an organic acid such as adipic acid, sebacic acid or azelaic acid with a straight-chain or branched alcohol containing 4 to 8 carbon atoms.

[0113] As typical examples of said organic ester plasticizers which can be suitably used, there may be mentioned triethylene glycol di-2-ethylbutyrate, triethylene glycol di-2-ethylhexoate, triethylene glycol dicaprylate, triethylene glycol di-n-octoate, triethylene glycol di-n-heptoate, tetraethylene glycol di-n-heptoate and, further, dibutyl sebacate, dioctyl azelate and dibutylcarbitol adipate.

[0114] In addition, ethylene glycol di-2-ethylbutyrate, 1,3-propylene glycol di-2-ethylbutyrate, 1,4-propylene glycol di-2-ethylbutyrate, 1,4-butylene glycol di-2-ethylbutyrate, 1,2-butylene glycol di-2-ethylenebutyrate, diethylene glycol di-2-ethylbutyrate, diethylene glycol di-2-ethylhexoate, dipropylene glycol di-2-ethylbutyrate, triethylene glycol di-2-ethylpentoate, tetraethylene glycol di-2-ethylbutyrate, diethylene glycol dicaprylate may also be used as the plasticizer.

[0115] Among the phosphate plasticizers, tributoxyethyl phosphate, isodecylphenyl phosphate, triisopropyl phosphite are preferred.

[0116] Among the plasticizers mentioned above, diester compounds derived from a dicarboxylic acid and a monohydric alcohol or from a monocarboxylic acid and a dihydric alcohol are preferably incorporated in the resin composition.

[0117] The addition amount of said plasticizer is preferably 20 to 70 parts by weight, more preferably 40 to 60 parts by weight, per 100 parts by weight of the poly(vinyl acetal) resin. At an addition amount below 20 parts by weight, the penetration resistance of the product laminated glass may be low. At an addition amount exceeding 70 parts by weight, the plasticizer may bleed out, increasing the optical strain or decreasing the transparency and/or tackiness of the resin film.

[0118] In the present invention, known additives for use in interlayer films for laminated glass, for example modified silicone oils for controlling penetration resistance, ultraviolet absorbers, light stabilizers, antioxidants, surfactants and coloring agent, may also be incorporated as additives in addition to said dispersant and bond strength control agent.

[0119] The modified silicone oils mentioned above include but are not limited to epoxy-modified silicone oils, ether-modified silicone oils, ester-modified silicone oils, amine-modified silicone oils and carboxyl-modified silicone oils, such as disclosed in Japanese Kokoku Publication Sho-55-29950. Generally, these modified silicone oils are liquids obtained by reacting a compound to be modified to polysiloxane.



20



35



50

55

55

55

blushing due to moisture absorption will be insufficient. At an addition amount exceeding 0.2 part by weight, the compatibility with the resin will be poor, hence bleeding will occur onto the film surface, with the result that the bond strength to glass will decrease. A more preferred amount is 0.03 to 0.1 part by weight.

[0124] The above-mentioned antioxidant includes but is not limited to such phenolic compounds as t-butylhydroxytoluene (BHT) (Sumilizer BHT (trademark), product of Sumitomo Chemical), and tetrakis[methylene-3-(3',5'-di-t-butyl-4'-hydroxyphenyl)propionato]methane (Irganox 1010, product of Ciba-Geigy).

[0125] Said ultraviolet absorbers include but are not limited to benzotriazole type such as 2-(2'-hydroxy-5'-methylphenyl)benzotriazole (Tinuvin P, product of Ciba-Geigy), 2-(2'-hydroxy-3'-5'-di-t-butylphenyl)benzotriazole (Tinuvin 320, product of Ciba-Geigy), 2-(2'-hydroxy-3'-t-butyl-5'-methylphenyl)-5-chlorobenzotriazole (Tinuvin 326, product of Ciba-Geigy) and 2-(2'-hydroxy-3',5'-di-t-amylphenyl)benzotriazole (Tinuvin 328, product of Ciba-Geigy), hindered amines such as LA-57 (product of Adeka-Argus).

[0126] As said light stabilizers, there may be mentioned hindered amines, for example Asahi Denka Kogyo's Adekastab LA-57 (trademark).

[0127] As said surfactants, there may be mentioned, for example, sodium lauryl sulfate, alkylbenzenesulfonates, and the like.

[0128] The method of producing the interlayer film for laminated glass of the present invention is particular restricted, but for example, a required amount of the plasticizer, together with other additives as necessary, is incorporated into each of the resins mentioned above, the mixture is kneaded uniformly and then formed into sheets by means of the extrusion, calendering, pressing, casting, inflation or other methods and the resulting sheets are used as interlayer films.

[0129] In view of the minimum penetration resistance and weather resistance required of laminated glass and from the practical viewpoint, it is generally preferred that the total thickness of the interlayer film for laminated glass of the present invention be within the range of 0.3 to 1.6 mm, which is the thickness range of ordinary interlayer film for laminated glasses.

[0130] As the glass sheets to be used in the laminated glass, there may be mentioned not only transparent inorganic glass sheets but also transparent organic glass sheets, such as polycarbonate sheets and poly(methyl methacrylate) sheets.

[0131] The transparent inorganic glass sheets are not limited to any particular species but include various inorganic glass species such as float sheet glass, polished sheet glass, embossed sheet glass, net sheet glass, wire sheet glass, infrared absorption glass and colored sheet glass. These may be used singly or two or more different species may be used in combination. Laminates of a transparent inorganic glass sheet and a transparent organic glass sheet may also be used. The glass sheet thickness can be suitably selected according to the intended use, hence is not limited to any particular value.

[0132] The laminated glass of the present invention can be produced by employing any ordinary method of producing laminated glass. For example, the resin film formed by the above-mentioned method is sandwiched, as the interlayer, between two transparent glass sheets, the whole is placed in a rubber bag, preliminary bonding is effected at about 70 to 110°C while suctioning under reduced pressure, then post-bonding is effected at about 120 to 150°C under a pressure of about 10 to 15 kg/cm² using an autoclave or a press, whereby the objective laminated glass is obtained.

[0133] In a process for producing laminated glass, it is also possible to interpose the above-mentioned interlayer film prepared by sheet formation from the plasticized poly(vinyl butyral) resin between at least one pair of glass sheets, and hot-press bonding at 60 to 100°C while simultaneously deaerating under reduced pressure. More concretely, the process is carried out by placing a laminate film consisting of a glass sheet/interlayer film/glass in a rubber bag, and effecting hot-press bonding at a temperature of about 60 to 100°C under a pressure of about 1 to 10 kg/cm² for about 10 to 30 minutes in an autoclave, for instance, while deaerating under suction at a reduced pressure of about -500 to -700 mmHg, to thereby realize deaeration and bonding simultaneously.

[0134] In such production process, the bond strength between the interlayer film and glass can be adjusted so that said strength will fall within a desired adequate range by adjusting the temperature for hot-press bonding to the range of 60 to 100°C, as mentioned above, and suitably selecting various conditions, in particular the hot-press bonding pressure, hot-press bonding time and extent of pressure reduction for deaeration under suction within the respective ranges mentioned above.

BEST MODES FOR CARRYING OUT THE INVENTION

[0135] The following examples illustrate the present invention in further detail but are by no means limitative of the scope of the invention. In the examples, "part(s)" means "part(s) by weight".

Example 1

(1) Preparation of a resin

[0136] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

[0137] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water for 2 hours and dried to provide a poly(vinyl butyral) resin as white powder. This resin had a vinyl acetal content (degree of acetalization) of 65.0 mole % and a vinyl acetate content of 1.1 mole %.

(2) Production of an interlayer film

[0138] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the blend was thoroughly melt-kneaded with a mixing roll and press-molded with a pressing machine at 150°C for 30 minutes to provide an interlayer film of 0.76 mm in thickness. The particle diameters of sodium and potassium salts in the interlayer film were determined by secondary ion imaging with a time-of-flight secondary ion mass spectrometer (TOF-SIMS) (PHI EVANS; TFS-2000). As a result, the particle diameter of the sodium salt in the interlayer film was 1 µm and that of the potassium salt was less than 0.5 µm.

[0139] The elemental sodium content of this interlayer film was 6 ppm as measured by ICP emission spectrometry. ICP emission spectrometry is a quantitative method of analysis which comprises decomposing a sample with sulfuric acid and nitric acid under heating, making the decomposition product up to constant volume with ultrapure water, and performing a determination by the ICP-AES method using an ICP-AES (Jarrel-Ash Japan, ICAP-575).

(3) Production of a laminated glass

[0140] The above interlayer film was sandwiched between transparent float glass sheets (30 cm x 30 cm x 2.5 mm thick) and the assembly was placed in a rubber bag and deaerated under a vacuum of 20 Torr for 20 minutes. The sample thus deaerated was directly transferred to an oven at 90°C and pressed under vacuum at a constant temperature of 80°C for 30 minutes.

[0141] The prebonded laminated glass was autoclaved using a pneumatic autoclave at a pressure of 12 kg/cm² and a temperature of 135°C for 20 minutes to provide a transparent laminated glass. This laminated glass was subjected to an adhesion test (Pummel test) and a moist blushing resistance test.

Performance evaluation

(1) Bonding power (Pummel) test

[0142] The laminated glass is left standing at -18°C ± 0.6°C for conditioning and then stricken with a hammer having a head weight of 0.45 kg to crush the glass to fragments with diameters not greater than 6 mm. The extent of exposure of the sheet after partial exfoliation of the glass is assessed against the graded limit samples shown in Table 1. This test is designed to find whether the bond strength between the glass and the interlayer film lies within a predetermined range.

Table 1

Extent of exposure (%)	Pammer value
100	0
90	1
85	2
60	3
40	4

Table 1 (continued)

Extent of exposure (%)	Pammer value
20	5
10	6
5	7
Less than 2	8

(2) Moist blushing resistance test

[0143] The resin film is cut to 4x4 cm and immersed in deionized water at room temperature (23°C) for 24 hours. The haze value was then measured with an integrating turbidimeter (Tokyo Denshoku). The results are shown in Table 2.

Example 2

[0144] The procedure of Example 1 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 1.5 hours. In this case, the interlayer film obtained had an elemental sodium content of 13 ppm, a sodium salt particle diameter of 3 μm , and a potassium salt particle diameter of not greater than 0.5 μm .

Example 3

[0145] The procedure of Example 1 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 2.5 hours. In this case, the interlayer film obtained had an elemental sodium content of 3 ppm, a sodium salt particle diameter of 0.5 μm , and a potassium salt particle diameter of not greater than 0.5 μm .

Example 4

[0146] The procedure of Example 1 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 3.5 hours. In this case, the interlayer film obtained had an elemental sodium content of 0.9 ppm, a sodium salt particle diameter of not greater than 0.5 μm , and a potassium salt particle diameter of not greater than 0.5 μm .

Comparative Example 1

[0147] The procedure of Example 1 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 1 hours. In this case, the interlayer film obtained had an elemental sodium content of 17 ppm and a sodium salt particle diameter of 6 μm .

Comparative Example 2

[0148] The procedure of Example 1 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 0.5 hours. In this case, the interlayer film obtained had an elemental sodium content of 35 ppm and a sodium salt particle diameter of 13 μm .

[0149] The evaluation data generated in Examples 1 to 4 and Comparative Examples 1 and 2 are presented in Table 2.

Table 2

		Example				Comp. Ex.	
		1	2	3	4	1	2
Interlayer film	Number of carbon in acetal	4	4	4	4	4	4
	Degree of acetalization (mol%)	65.0	65.0	65.0	65.0	65.0	65.0
	Average degree of polymerization	1700	1700	1700	1700	1700	1700
	Vinylacetate content (mol %)	1.1	1.1	1.1	1.1	1.1	1.1
	Plasticizer content (weight parts)	40	40	40	40	40	40
	Na content (ppm)	6	13	3	0.9	17	35
	Particle diameter of Na (μm)	1	3	0.5	0.5>	6	13
	K content (ppm)	0.5	0.6	0.5	0.5	-	-
	Particle diameter of K (μm)	0.5>	0.5>	0.5>	0.5>	-	-
Bonding strength of a laminated glass (Pammer value)		8	8	8	8	8	8
Haze after 24 hours immersion (%)		29	37	24	16	67	92
Total evaluation		○	○	○	○	×	×

[0150] It is apparent that very satisfactory moisture resistance was obtained in Examples 1 to 4.

Example 5

(1) Preparation of a resin

[0151] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

[0152] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess (30 times the resin) of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous potassium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water for 2 hours and dried to provide a poly(vinyl butyral) resin as white powder.

[0153] This resin had a vinylacetal content (degree of acetalization) of 65.0 mole % and a vinyl acetate content of 1.1 mole %.

(2) Production of an interlayer film

[0154] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the blend was thoroughly melt-kneaded with a mixing roll and press-molded with a pressing machine at 150°C for 30 minutes to provide an interlayer film of 0.76 mm in thickness.

[0155] The elemental potassium content of this interlayer film was 23 ppm as measured by ICP emission spectrometry. The particle diameter of the sodium salt in the interlayer film was less than 0.5 μm and that of the potassium salt was less than 3 μm .

(3) Production of a laminated glass

[0156] The above interlayer film was sandwiched between transparent float glass sheets (30 cm x 30 cm x 2.5 mm thick) and the assembly was placed in a rubber bag and deaerated under a vacuum of 20 Torr for 20 minutes. The sample thus deaerated was directly transferred to an oven at 90°C and pressed at a constant temperature of 80°C for 30 minutes.

[0157] The prebonded laminated glass was autoclaved using a pneumatic autoclave at a pressure of 12 kg/cm² and

a temperature of 135°C for 20 minutes to provide a transparent laminated glass.

Example 6

- 5 [0158] The procedure of Example 5 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 2.5 hours. In this case, the interlayer film obtained had an elemental potassium content of 5 ppm, a potassium salt particle diameter of 1 μm , and a sodium salt particle diameter of not greater than 0.5 μm .

10 Example 7

- [0159] The procedure of Example 5 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 3.5 hours. In this case, the interlayer film obtained had an elemental potassium content of 0.7 ppm, a potassium salt particle diameter of not greater than 0.5 μm , and a sodium salt particle diameter of not greater than 0.5 μm .

Comparative Example 3

- 20 [0160] The procedure of Example 5 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 1 hour. In this case, the interlayer film obtained had an elemental potassium content of 104 ppm and a potassium salt particle diameter of 6 μm .

Comparative Example 4

- 25 [0161] The procedure of Example 5 was repeated except that, in the preparation of the resin, the washing process time following addition of the neutralizing agent was altered to 0.5 hour. In this case, the interlayer film obtained had an elemental potassium content of 220 ppm and a potassium salt particle diameter of 9 μm .
[0162] The laminated glasses obtained in Examples 5 to 8 and Comparative Examples 3 and 4 were respectively subjected to a bonding power (Pummel) test and a moisture resistance test under the same conditions as described above. The results of evaluation are collectively presented in Table 3.

Table 3

		Example			Comp.Ex.	
		5	6	7	3	4
35	Interlayer film	Number of carbon in acetal	4	4	4	4
		Degree of acetalizat ion (mol%)	65.0	65.0	65.0	65.0
		Avarage degree of polymerization	1700	1700	1700	1700
		Vinylacetate content (mol%)	1.1	1.1	1.1	1.1
		Plasticizer content (weight parts)	40	40	40	40
		K content (ppm)	23	5	0.7	104
		Particle diameter of K (μm)	3	1	0.5>	6
		Na content (ppm)	0.7	0.6	0.8	-
		Particle diameter of Na (μm)	0.5>	0.5>	0.5>	-
50	Bonding strength of a laminated glass (Pammer value)		8	8	8	7
	Haze after 24 hours of immersion (%)		24	20	14	60
	Total evaluation		○	○	○	×

- 55 [0163] It will be apparent that very satisfactory moisture resistance was obtained in Examples 5 to 7.

Example 8

(1) Preparation of a resin

5 [0164] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

10 [0165] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water and dried to provide a poly(vinyl butyral) resin as white powder. This resin had a vinyl acetal content (degree of acetalization) of 65.0 mole %.

15 (2) Production of an interlayer film

[0166] The above polybutyral resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film as determined with an ICP emission spectrometric elemental analyzer was 13 ppm. The particle diameter of sodium salt in the interlayer film was 3 µm.

(3) Production of a laminated glass

25 [0167] The above interlayer film was sandwiched between two 2.5 mm thick float glass sheets and the assembly was placed in a rubber bag and effected hot-press bonding at a temperature of 60°C and a pressure of 5 kg/cm² under suction degassing at a reduced pressure of -600 mmHg in an autoclave for 20 minutes to provide a laminated glass.

Example 9

30 [0168] Except that the hot-press bonding temperature for the fabrication of a laminated glass was altered to 80°C, the procedure of Example 8 was otherwise repeated to provide a laminated glass. The particle diameter of the sodium salt in the interlayer film was 3 µm.

Example 10

35 [0169] Except that the hot-press bonding temperature for the fabrication of a laminated glass was altered to 100°C, the procedure of Example 8 was otherwise repeated to provide a laminated glass. The particle diameter of the sodium salt in the interlayer film was 3 µm.

40 Comparative Example 5

[0170] Except that the hot-press bonding temperature for the fabrication of a laminated glass was altered to 80°C, the procedure of Example 8 was otherwise repeated to provide a laminated glass. The sodium content of the obtained interlayer film was 30 ppm and the particle diameter of the sodium salt thereof was 11 µm.

45 [0171] The glass laminates obtained in Examples 8 to 10 and Comparative Example 5 were respectively subjected to a bonding power (Pummel) test and a heat resistance test under the following conditions. A moisture resistance test was also performed using the same conditions as in Example 1.

Evaluation Methods

50

(1) Bonding power (Pummel) test

[0172] The laminated glass is cooled at -20°C for 2 hours and, then, mounted on an automatic hammering machine. The whole surface of the laminated glass is uniformly stricken with the hammer head and the area of glass fragments adhering to the interlayer film is visually assessed against the graded limit samples shown in Table 1 to evaluate the bonding power (Pummel value). The graded limit sample is based on a 10-point scale giving 1 point for minimum adhesion and 10 points for maximum adhesion. The automatic hammering machine used is equipped with a hammer head having a curved bottom surface having a radius of curvature of 50 mm and an effective striking diameter of 5 mm

and weighing 240 g and the impact force of the hammer head is adjustable with a spring screw.

(2) Heat resistance test

5 [0173] In conformity with JIS R3205 "Laminated Glass", the sample laminated glass is left standing in an atmosphere at 130°C for 2 hours and then taken out and the presence or absence of air cells is visually examined.

[0174] The results obtained in Examples 8 to 10 and Comparative Example 5 are collectively shown in Table 4.

Table 4

	Example			Compar. Ex.
	8	9	10	5
Na content (ppm)	13	13	13	30
Particle diameter of Na (μm)	3	3	3	11
Bonding strength of the laminated glass (Pammer value)	1	5	8	5
Haze after 24 hours of immersion (%)	37	38	33	66
Presence or absence of air form after Heat resistance test	none	none	none	none
Total evaluation	○	○	○	×

Example 11

25 (1) Preparation of a resin

[0175] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

30 [0176] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess (30 times the resin) of water to remove the unreacted n-butyraldehyde. The pH of the system at this stage was found to be pH 5.1. The system was then dehydrated with Centor dehydrating machine to provide a resin of 50% water content. This resin was dried in an atmosphere at 60°C and -700 mmHg to provide a poly(vinyl butyral) resin as white powder. The acetalization rate of this resin was 65.0 mole %.

(2) Production of an interlayer film

40 [0177] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film as determined with an ICP emission spectrometric elemental analyzer was 0.7 ppm. The particle diameter of sodium salt in the interlayer film was less than 0.5 μm.

(3) Production of a laminated glass

45 [0178] The above interlayer film was sandwiched between two 2.5 mm thick float glass sheets and the assembly was placed in a rubber bag and hot-pressed at a temperature of 60°C and a pressure of 5 kg/cm² under suction degassing at a reduced pressure of -600 mmHg in an autoclave for 20 minutes to provide a laminated glass.

50 Example 12

(1) Preparation of a resin

55 [0179] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

[0180] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction

mixture was washed with an excess (30 times the resin) of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. Then, the reaction product was rinsed with an excess (30 times the resin) of water at 50°C and dried to provide a poly (vinyl butyral) resin as white powder. The degree of acetalization of this resin was 65.0 mole %.

(2) Production of an interlayer film.

[0181] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film as determined with an ICP emission spectrometric elemental analyzer was 10 ppm. The particle diameter of sodium salt in the interlayer film was 3 µm.

(3) Production of a laminated glass

[0182] The above interlayer film was sandwiched between two 2.5 mm thick float glass sheets and the assembly was placed in a rubber bag and hot-pressed at a temperature of 60°C and a pressure of 5 kg/cm² under suction degassing at a reduced pressure of -600 mmHg in an autoclave for 20 minutes to provide a laminated glass.

Example 13

[0183] Except that post-neutralization washing was carried out with water at 60°C, the procedure of Example 12 was otherwise repeated to provide an interlayer film. The rate of acetalization of this interlayer film was 65.0 mole %. The elemental sodium content of this interlayer film was 15 ppm as determined with an ICP emission spectrometric elemental analyzer. The particle diameter of sodium salt in this interlayer film was 4 µm.

Example 14

(1) Preparation of a resin

[0184] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

[0185] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous magnesium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water and dried to provide a poly(vinyl butyral) resin as white powder.

(2) Production of an interlayer film.

[0186] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate, and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film as determined with an ICP emission spectrometric elemental analyzer was 0.7 ppm. The particle diameter of sodium salt in the interlayer film was less than 0.5 µm.

(3) Production of a laminated glass

[0187] The above interlayer film was sandwiched between two 2.5 mm thick float glass sheets and the assembly was placed in a rubber bag and hot-pressed at a temperature of 60°C and a pressure of 5 kg/cm² under suction degassing at a reduced pressure of -600 mmHg in an autoclave for 20 minutes to provide a laminated glass.

[0188] The glass laminates obtained above in Examples 11 to 14 were respectively subjected to the following heat resistance test. In addition, a moisture resistance test was carried out in the same manner as in Example 1. However, the product of Example 14 was subjected to the moisture resistance test only.

Methods of Evaluation

(1) Heat resistance test

5 **[0189]** One gram of the resin was placed in an ordinary test tube and heated in an oil bath at 150°C for 60 minutes to assess the possible degradation of the resin.

[0190] The data obtained in Examples 11 to 14 are collectively presented in Table 5.

Table 5

	Example			
	11	12	13	14
Na content (ppm)	0.7	10	15	0.7
Particle diameter of Na (μm)	0.5>	3	4	0.5>
Heat resistance test	O.K.	O.K.	O.K.	-
Haze after 24 hours of immersion (%)	13	32	39	24
Total evaluation	○	○	○	-

Example 15

(1) Preparation of a resin

25 **[0191]** To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700, a saponification degree of 98.9 mole % and 0.1 weight % of sodium acetate, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butylaldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product.

30 **[0192]** The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess (30 times the resin) of water to remove the unreacted n-butylaldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water and dried to provide a poly(vinyl butyral) resin as white powder.

[0193] The acetalization degree of this resin was 65 mole %.

(2) Production of an interlayer film

35 **[0194]** The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film was 8 ppm as determined with an ICP emission spectrometric
40 elemental analyzer.

Example 16

45 **[0195]** Except that 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700, a saponification degree of 98.9 mole %, and a sodium acetate content of 0.4 weight %, the procedure of Example 15 was otherwise repeated to provide an interlayer film. The degree of acetalization of this interlayer film was 65.0 mole %. The elemental sodium content of this interlayer film was 13 ppm as determined with an ICP emission spectrometric elemental analyzer.

Example 17

(1) Preparation of a resin

50 **[0196]** To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700, a saponification degree of 98.9 mole % and a sodium acetate content of 0.1 weight %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% hydrochloric acid catalyst and 148 g of n-butylaldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction
55 product.

[0197] The reaction mixture was then held at 45°C for 3 hours to carry the reaction to completion. This reaction mixture was washed with an excess (30 times the resin) of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with magnesium octanoate. The product was rinsed with an excess of water and dried to provide a poly(vinyl butyral) resin as white powder. The acetalization degree of this resin was 65 mole %.

(2) Production of an interlayer film

[0198] The above poly(vinyl butyral) resin, 100 weight parts, was blended with 40 weight parts of the plasticizer triethylene glycol di-2-ethylbutyrate and the mixture was press-molded with a pressing machine to provide an interlayer film. The elemental sodium content of this interlayer film was 2 ppm as determined with an ICP emission spectrometric elemental analyzer.

Example 18

[0199] Except that ethylene oxide was used as the neutralizer of the hydrochloric acid catalyst, the procedure of Example 17 was otherwise repeated to provide an interlayer film. The degree of acetalization of this interlayer film was 65 mole %. The elemental sodium content of this interlayer film was 2 ppm as determined with an ICP emission spectrometric elemental analyzer.

[0200] The interlayer films obtained in Examples 15-18 were respectively subjected to a heat resistance test as in Example 11 and a moisture resistance test as in Example 1. The results are presented in Table 6.

Table 6

	Example			
	15	16	17	18
Sodium acetate content in poly(vinyl alcohol) (wt.%)	0.1	0.4	0.1	0.1
Na content (ppm)	8	13	2	2
Particle diameter of Na (μm)	0.6	2	0.5>	0.5>
Heat resistance test	O.K.	O.K.	O.K.	O.K.
Haze after 24 hours of immersion (%)	19	35	11	10
Total evaluation	○	○	○	○

Example 19

(1) Preparation of a poly(vinyl acetal) resin

[0201] To 2890 g of pure water was added 275 g of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 98.9 mole %, and the mixture was warmed for dissolving. After the reaction system was adjusted to 12°C, 201 g of 35% weight hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product. The reaction mixture was then washed with an excess of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water for 2 hours and dried to provide a poly(vinyl butyral) resin as white powder. This resin had an average butyralization degree of 64 mole % and a residual acetyl group content of 1 mole %.

(2) Production of an interlayer film for laminated glass

[0202] To 100 parts of the above poly(vinyl butyral) resin (average degree of polymerization: 1700, average butyralization degree: 64 mole %, residual acetyl group content: 1 mole %) were added 40 parts of the plasticizer triethylene glycol di-2-ethylbutyrate and 0.08 part of magnesium octanoate as the bond strength control agent. The mixture was thoroughly melt-kneaded with a mixing roll and press-molded with a pressing machine at 150°C for 30 minutes to provide an interlayer film for laminated glass having an average thickness of 0.76 mm.

[0203] This interlayer film for laminated glass had a sodium content of 10 ppm and a sodium salt particle diameter of 1 μm. The particle diameter of magnesium salt in the interlayer film was 0.9 μm as determined with a time-of-flight

secondary ion mass spectrometer (TOF-SIMS).

(3) Production of a laminated glass

[0204] The above interlayer film for laminated glass was sandwiched between transparent float glass sheets (30 cm x 30 cm x 3 mm thick) and the assembly was placed in a rubber bag and deaerated under a vacuum of 20 Torr for 20 minutes. The deaerated assembly was directly transferred to an oven and pressed under vacuum at 90°C for 30 minutes.

[0205] The prebonded laminated glass thus obtained was further subjected to post-bonding in a pneumatic autoclave at a temperature of 135°C and a pressure of 12 kg/cm² for 20 minutes to provide a laminated glass.

Example 20

[0206] Except that, in the production of an interlayer film for laminated glass, 0.09 part of magnesium neodecanoate was used in lieu of 0.08 part of magnesium octanoate as the bond strength control agent, the procedure of Example 19 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0207] The particle diameter of magnesium salt in the interlayer film for laminated glass obtained in the above manner was 0.5 µm as determined by the same method as in Example 19.

Example 21

[0208] Except that, in the production of an interlayer film for laminated glass, 0.04 part of magnesium chloride was used in lieu of 0.08 part of magnesium octanoate as the bond strength control agent, the procedure of Example 19 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0209] The particle diameter of magnesium salt in the interlayer film for laminated glass obtained in the above manner was 2 µm as determined by the same method as in Example 19.

Example 22

[0210] Except that, in the production of a poly(vinyl acetal) resin, basic magnesium carbonate was used in lieu of aqueous sodium hydroxide solution as the neutralizing agent, the procedure of Example 19 was otherwise repeated to provide a white powdery poly(vinyl butyral) resin with an average polymerization degree of 1700, an average butyralization degree of 64 mole %, and a residual acetyl group content of 1 mole %.

[0211] Then, an interlayer film for laminated glass and a laminated glass were prepared in substantially the same manner as in Example 19 except that, in the preparation of the interlayer film for laminated glass, 100 parts of the above poly(vinyl butyral) resin was used in lieu of 100 parts of the poly(vinyl butyral) resin prepared in Example 19 and the addition of 0.08 part of magnesium octanoate as the bond strength control agent was omitted.

[0212] This interlayer film had a sodium content of 0.7 ppm and a sodium salt particle diameter of not greater than 0.5 µm. The particle diameter of magnesium salt in this interlayer film was 2 µm as determined in the same manner as in Example 19.

Example 23

[0213] Except that, in the preparation of poly(vinyl acetal) resin, aqueous magnesium hydroxide solution was used in lieu of aqueous sodium hydroxide solution as the neutralizing agent, the procedure of Example 19 was otherwise repeated to provide a white powdery poly(vinyl butyral) resin with an average polymerization degree of 1700, an average butyralization degree of 64 mole % and a residual acetyl group content of 1 mole %.

[0214] Then, an interlayer film for laminated glass and a laminated glass were prepared in substantially the same manner as in Example 19 except that 100 parts of the above poly(vinyl butyral) resin was used in lieu of 100 parts of the poly(vinyl butyral) resin obtained in Example 19 and the addition of 0.08 part of magnesium octanoate as the bond strength control agent was omitted in the preparation of the interlayer film.

[0215] This interlayer film had a sodium content of 0.7 ppm and a sodium salt particle diameter of not greater than 0.5 µm. The particle diameter of magnesium salt in this interlayer film was 2.5 µm as determined in the same manner as in Example 19.

Comparative Example 6

[0216] Except that 0.04 part of magnesium acetate, which is sparingly soluble in poly(vinyl butyral) resin and plas-

ticizer, was used in lieu of 0.08 part of magnesium octanoate as the bond strength control agent in the preparation of an interlayer film for laminated glass, the procedure of Example 19 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0217] The particle diameter of magnesium salt in the interlayer film for laminated glass obtained in the above manner was 10 μm as determined by the same method as in Example 19.

Comparative Example 7

[0218] Except that 0.04 part of magnesium acetate which is sparingly soluble in poly(vinyl butyral) resin and plasticizer and 0.05 parts of butyric acid which is short-chain organic acid were used in lieu of 0.08 part of magnesium octanoate as the bond strength control agent in the preparation of an interlayer film for laminated glass, the procedure of Example 19 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0219] The particle diameter of magnesium salt in the interlayer film for laminated glass obtained in the above manner was 4 μm as determined by the same method as in Example 19.

[0220] The interlayer film for laminated glasses obtained in Examples 19 to 23 and Comparative Examples 6 and 7 were respectively subjected to a moisture resistance test as in Example 1. The results are presented in Table 7.

Table 7

		Example					Comp. Ex.	
		19	20	21	22	23	6	7
	Number of carbon in acetal	4	4	4	4	4	4	4
	Average degree of butyralization (mole%)	64.0	64.0	64.0	64.0	64.0	64.0	64.0
	Residual acetyl group content (mole%)	1.0	1.0	1.0	1.0	1.0	1.0	1.0
	Average degree of polymerization	1700	1700	1700	1700	1700	1700	1700
	Plasticizer (wt. parts)	40	40	40	40	40	40	40
	Na content (ppm)	10	10	10	0.7	0.7	10	10
	Particle diameter of Na (μm)	1.0	1.0	1.0	0.5>	0.5>	1.0	1.0
	Addition amount of magnesium salt(wt, parts)	0.08	0.09	0.04	0	0	0.04	0.04
	Particle diameter of magnesium salt (μm)	0.9	0.5	2.0	2.0	2.5	10.0	4.0
	Haze after 24 hours of immersion (%)	19.0	16.4	26.8	28.4	38.3	92.0	67.2
	Total evaluation	○	○	○	○	○	×	×

[0221] It will be apparent from Table 7 that the laminated glasses according to Examples 19 to 23 of the invention have excellent moisture resistance. In contrast, the glass laminates according to Comparative Examples 6 and 7, in which the particle diameters of magnesium salt contained in the interlayer films were over 3 μm , showed poor moisture resistance.

Example 24

Synthesis and production

(Synthesis of poly(vinyl butyral) resin)


[0222] A reactor equipped with a stirring means was charged with 2900 weight parts of deionized water and 198 weight parts of a poly(vinyl alcohol) with an average polymerization degree of 1700 and a saponification degree of 99.2 mole % (corresponding to 4.5 mols of vinyl alcohol) and the charge was heated to 95°C with stirring for dissolving. After this solution was cooled to 30°C, 208 weight parts (2.1 moles) of 35 weight % hydrochloric acid and 152 weight parts (2.1 moles) of n-butyraldehyde were added. After the liquid temperature was lowered to 2°C, the reaction system was maintained at this temperature to precipitate the poly(vinyl butyral) resin. The liquid temperature was then raised to 30°C and maintained at this level for 5 hours. Thereafter, the reaction mixture was neutralized with 156 weight parts (1.8 moles) of sodium hydrogencarbonate, washed with water and dried to provide a poly(vinyl butyral) resin with a butyralization degree of 65 mole %.

[0223] The sodium content of this poly(vinyl butyral) resin was 50 ppm as determined by ICP emission spectrometry. The particle diameter of the sodium salt was 12 μm .

(Production of a resin film)

[0224] One hundred (100) weight parts of the poly(vinyl butyral) resin obtained as above, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.05 weight part of ethylenediaminetetraacetic acid, 0.04 weight part of magnesium 2-ethylbutyrate and 0.05 weight part of modified silicone oil were fed to a mixing roll and kneaded. Using a pressing machine, this kneaded material was press-molded at 150°C and 120 kg/cm² for 30 minutes to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moisture resistance test as in Example 1.

[0225] As the modified silicone oil, the oil of the following chemical formula was used.



Example 25

[0226] A resin film was prepared and evaluated in the same manner as in Example 24 except that 0.08 weight part of salicylaldehyde was used in lieu of 0.05 weight part of ethylenediaminetetraacetic acid. The results are shown in Table 8.

Example 26

[0227] A resin film was prepared and evaluated in the same manner as in Example 24 except that 1.0 weight part of oxalic acid was used in lieu of 0.05 weight part of ethylenediaminetetraacetic acid. The results are shown in Table 8.

Example 27

[0228] A resin film was prepared and evaluated in the same manner as in Example 24 except that 0.03 weight part of 1,10-phenanthroline was used in lieu of 0.05 weight part of ethylenediaminetetraacetic acid. The results are shown in Table 8.

Example 28

[0229] A resin film was prepared and evaluated in the same manner as in Example 24 except that 0.3 weight part of acetylacetone was used in lieu of 0.05 weight part of ethylenediaminetetraacetic acid. The results are shown in Table 8.

Comparative Example 8

[0230] A resin film was prepared and evaluated in the same manner as in Example 24 except that 0.05 weight part of ethylenediaminetetraacetic acid was not used. The results are shown in Table 8.

Comparative Example 9

[0231] A resin film was prepared and evaluated in the same manner as in Example 24 except that 0.3 weight part of acetone was used in lieu of 0.05 weight part of ethylenediaminetetraacetic acid. The results are shown in

Table 8

	Butyral resin (wt. parts)	Diester compound (wt. parts)	Complex forming compound		Mg salt of carboxylate (wt.)	Modified silicone oil (wt.)	Haze after 24 hours of immersion (%)
			kind	wt.			
24	100	40	Ethylenediaminetetraacetic acid	0.05	0.04	0.05	26.0
25	100	40	Salicylaldehyde	0.08	0.04	0.05	29.5
26	100	40	oxalic acid	1.0	0.04	0.05	35.6
27	100	40	1,10-phenanthroline	0.03	0.04	0.05	39.5
28	100	40	acetylacetone	0.3	0.04	0.05	36.9
8	100	40	none	—	—	0.05	77.0
9	100	40	acetone	0.1	—	0.05	92.0
Example							
Compar. Example							

Example 29

(1) Preparation of poly(vinyl acetal) resin

[0232] In 2890 g of pure water was dissolved 275 g of a poly(vinyl alcohol) having an average polymerization degree of 1700 and a saponification degree of 98.9 mole % under heating. After this reaction system was adjusted to 12°C, 201 g of 35 weight % hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at this temperature to precipitate the reaction product. This reaction system was held at 45°C for 3 hours to carry the

reaction to completion. The reaction mixture was then washed with an excess of water to remove the unreacted n-butyraldehyde and the hydrochloric acid catalyst was neutralized with aqueous sodium hydroxide solution, the common neutralizing agent. The product was rinsed with an excess of water for 2 hours and dried to provide a white powdery poly(vinyl butyral) resin. This resin had an average butyralization degree of 64 mole % and a resin acetyl group content of 1 mole %.

(2) Production of an interlayer film for laminated glass

[0233] To 100 parts of the above poly(vinyl butyral) resin (average polymerization degree: 1700, average butyralization degree: 64 mole %, residual acetyl group content: 1 mole %) were added 40 parts of the plasticizer triethylene glycol di-2-ethylbutyrate, 0.75 part of dodecylbenzenesulfonic acid as the organic acid and 0.13 part of dimethyloctylamine as the amine. The mixture was thoroughly melt-kneaded with a mixing roll and press-molded with a pressing machine at 150°C for 30 minutes to provide an interlayer film for laminated glass having an average thickness of 0.76 mm.

[0234] The sodium content of the above interlayer film was 50 ppm as determined by ICP emission spectrometry. The particle diameter of elemental sodium in the interlayer film was 4 µm as determined by time-of-flight secondary ion mass spectrometry (TOF-SIMS).

(3) Production of a laminated glass

[0235] The above interlayer film was sandwiched between two transplant float glass sheets (30 cm x 30 cm x 3 mm thick) and the assembly was placed in a rubber bag and deaerated under a vacuum of 20 Torr for 20 minutes. The deaerated assembly was immediately transferred to an oven at 90°C and pressed under suction at a constant temperature of 80°C for 30 minutes.

[0236] The prebonded glass thus obtained was subjected to post-bonding in a pneumatic autoclave at 135°C and 12 kg/cm² for 20 minutes to provide a laminated glass.

[0237] The interlayer film for laminated glass thus obtained was subjected to a moisture resistance test as in Example 1. The results are shown in Table 9.

Example 30

[0238] A resin film was prepared and evaluated as in Example 29 except that 0.30 part of octanoic acid was added in lieu of 0.75 part of dodecylbenzenesulfonic acid as the organic acid and 0.35 part of decylamine in lieu of 0.13 part of dimethyloctylamine as the amine in the preparation of the interlayer film for laminated glass. The results are shown in Table 9.

[0239] The particle diameter of the elemental sodium in the above interlayer film was 5 µm as determined in the same manner as in Example 29.

Example 31

[0240] A resin film was prepared and evaluated as in Example 29 except that 0.20 part of di(2-ethylhexyl)phosphoric acid was added in lieu of 0.75 part of dodecylbenzenesulfonic acid as the organic acid in the preparation of the interlayer film for laminated glass. The results are shown in Table 9.

[0241] The particle diameter of the elemental sodium in the interlayer film was 2 µm as determined by the same method as in Example 29.

Comparative Example 10

[0242] A resin film was prepared and evaluated as in Example 29 except that the dispersant organic acid and amine were not added in the preparation of the interlayer film for laminated glass. The results are shown in Table 9.

[0243] The particle diameter of the elemental sodium in the above interlayer film was 20 µm as determined in the same manner as in Example 29.

Comparative Example 11

[0244] A resin film was prepared and evaluated as in Example 29 except that the addition of the dispersant organic acid and amine was omitted and the washing time was altered from 2 hours to 3 hours in the preparation of the interlayer film for laminated glass. The results are shown in Table 9.

[0245] The sodium content of the interlayer film was 30 ppm as determined by the same procedure as in Example 29. The particle diameter of the elemental sodium as determined by the same method as in Example 29 was 13 μm .

Table 9

		Example			Comp. Bx.	
		29	30	31	10	11
Interlayer film	Number of carbon in acetal	4	4	4	4	4
	Average degree of butyralization (mole%)	64.0	64.0	64.0	64.0	64.0
	Residual acetyl group content (mole%)	1.0	1.0	1.0	1.0	1.0
	Average degree of polymerization	1700	1700	1700	1700	1700
	Plasticizer (wt.parts)	40	40	40	40	40
	Na content (ppm)	50	50	50	50	30
	Particle diameter of Na (μm)	4	5	2	20	13
Haze after 24 hours of immersion(%)		26	28	20	92	72
Total evaluation		○	○	○	×	×

Example 32

Synthesis and sheet formation

(Synthesis of poly(vinyl butyral) resin)

[0246] A reactor equipped with a stirring means was charged with 2900 weight parts of deionized water, 198 weight parts of a poly(vinyl alcohol) having an average polymerization degree of 1700 and a saponification degree of 99.2 mole % (corresponding to 4.5 moles of vinyl alcohol) and the charge was heated at 95°C with stirring for dissolving. After this solution was cooled to 30°C, 196 weight parts (1.9 moles) of 35 weight % hydrochloric acid and 152 weight parts (2.1 moles) of n-butyraldehyde were added. After the liquid temperature was lowered to 2°C, the reaction mixture was incubated at this temperature to precipitate the poly(vinyl butyral) resin. The liquid temperature was then raised to 30°C and maintained at this level for 5 hours. Thereafter, the reaction mixture was neutralized with 147 weight parts (1.7 moles) of sodium hydrogencarbonate, washed with water and dried to provide a poly(vinyl butyral) resin with a butyralization degree of 65 mole %.

[0247] The sodium content of this poly(vinyl butyral) resin was 50 ppm as determined by ICP emission spectrometry. The particle diameter of sodium salt was 12 μm .

(Preparation of a resin film)

[0248] One hundred (100) weight parts of the above poly(vinyl butyral) resin, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine were fed to a mixing roll and kneaded. This kneaded material was press-molded with a pressing machine at 150°C and 120 kg/cm² for 10 minutes to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing resistance test as in Example 1. The results are shown in Table 10.

Example 33

[0249] A resin film was prepared and evaluated as in Example 32 except that 0.49 weight part of tetradecylamine was used in lieu of 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 34

[0250] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid was used in lieu of 0.43 weight % of p-toluenesulfonic acid. The results are shown in Table 10.

Example 35

[0251] A resin film was prepared and evaluated as in Example 32 except that 0.15 weight part of dodecylbenzenesulfonic acid and 0.07 weight part of decylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 36

[0252] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid and 0.36 weight part of decylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 37

[0253] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid and 0.42 weight part of dodecylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 38

[0254] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid and 0.55 weight part of N,N-diocetylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 39

[0255] A resin film was prepared and evaluated as in Example 32 except that 0.37 weight part of dodecylbenzenesulfonic acid and 0.18 weight part of N,N-dimethyloctylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 40

[0256] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid and 0.36 weight part of N,N-dimethyloctylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Example 41

[0257] A resin film was prepared and evaluated as in Example 32 except that 0.75 weight part of dodecylbenzenesulfonic acid and 0.49 weight part of N,N-dimethyldodecylamine were used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Comparative Example 12

[0258] A resin film was prepared and evaluated as in Example 32 except that the addition of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine was omitted. The results are shown in Table 10.

Comparative Example 13

[0259] A resin film was prepared and evaluated as in Example 32 except that the addition of 0.43 weight part of p-toluenesulfonic acid was omitted and 0.36 weight part of decylamine was used in lieu of 0.23 weight part of hexylamine. The results are shown in Table 10.

Comparative Example 14

[0260] A resin film was prepared and evaluated as in Example 32 except that the addition of 0.23 weight part of hexylamine was omitted. The results are shown in Table 10.

Comparative Example 15

[0261] A resin film was prepared and evaluated as in Example 32 except that 0.80 weight part of sodium dodecylbenzenesulfonate was used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Comparative Example 16

[0262] A resin film was prepared and evaluated as in Example 32 except that 0.33 weight part of dodecyltrimethylammonium chloride was used in lieu of 0.43 weight part of p-toluenesulfonic acid and 0.23 weight part of hexylamine. The results are shown in Table 10.

Table 10

	Sulfonic acid		Amine				Haze after 24 hours of immersion (%)
	Kind	addition amount	R ³	R ⁴	R ⁵	addition amount	
32	p-toluenesulfonic acid	0.43	hexyl	H	H	0.23	29.1
33	p-toluenesulfonic acid	0.43	tetra-decyl	H	H	0.49	18.6
34	dodecylbenzenesulfonic acid	0.75	hexyl	H	H	0.23	22.8
35	dodecylbenzenesulfonic acid	0.15	decyl	H	H	0.07	27.8
36	dodecylbenzenesulfonic acid	0.75	decyl	H	H	0.36	17.1
37	dodecylbenzenesulfonic acid	0.75	dodecyl	H	H	0.42	20.1
38	dodecylbenzenesulfonic acid	0.75	octyl	octyl	H	0.55	32.4
39	dodecylbenzenesulfonic acid	0.37	octyl	methyl	methyl	0.18	29.3
40	dodecylbenzenesulfonic acid	0.75	octyl	methyl	methyl	0.36	23.1
41	dodecylbenzenesulfonic acid	0.75	dodecyl	methyl	methyl	0.49	29.1
12	—	0	—	—	—	0	77.6
13	—	0	decyl	H	H	0.36	85.9
14	p-toluenesulfonic acid	0.43	—	—	—	0	resin degradation
15	Sodium dodecylbenzenesulfonate						76.8
16	Dodecyltrimethylammonium chloride						60.6

Example

Compar.
Example

Example 42

(Preparation of a poly(vinyl butyral) resin)

[0263] The poly(vinyl butyral) resin synthesized in Example 32 was further rinsed with water and dried to provide a poly(vinyl butyral) resin with reduced sodium salt content.

[0264] The sodium content of this poly(vinyl butyral) resin was 20 ppm as determined by ICP emission spectrometry. The particle diameter of the sodium salt was 3.5 μm .

(Preparation of a resin film)

[0265] One-hundred (100) weight parts of the poly(vinyl - butyral) resin obtained above, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine were kneaded together and press-molded under the same conditions as used in Example 32 to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing test as in Example 1. The results are shown in Table 11.

Example 43

[0266] A resin film was prepared and evaluated as in Example 42 except that 0.17 weight part of dodecylbenzenesulfonic acid and 0.09 weight part of decylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine.

Example 44

[0267] A resin film was prepared and evaluated as in Example 42 except that 0.03 weight part of dodecylbenzenesulfonic acid and 0.02 weight part of decylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine.

Example 45

[0268] A resin film was prepared and evaluated as in Example 42 except that 0.17 weight part of N,N-dimethyloctylamine was used in lieu of 0.17 weight part of decylamine. The results are shown in Table 11.

Example 46

[0269] A resin film was prepared and evaluated as in Example 42 except that 0.17 weight part of dodecylbenzenesulfonic acid and 0.09 weight part of N,N-dimethyloctylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

Example 47

[0270] A resin film was prepared and evaluated as in Example 42 except that 0.03 weight part of dodecylbenzenesulfonic acid and 0.02 weight part of N,N-dimethyloctylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

Example 48

[0271] A resin film was prepared and evaluated as in Example 42 except that 0.30 weight part of dodecylbenzenesulfonic acid and 0.20 weight part of N,N-dimethyldodecylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

Example 49

[0272] A resin film was prepared and evaluated as in Example 42 except that 0.12 weight part of dodecylbenzenesulfonic acid and 0.08 weight part of N,N-dimethyldodecylamine were used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

Comparative Example 17

[0273] A resin film was prepared and evaluated as in Example 42 except that the addition of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine were omitted. The results are shown in Table 11.

Comparative Example 18

[0274] A resin film was prepared and evaluated as in Example 42 except that the addition of 0.33 weight part of dodecylbenzenesulfonic acid was omitted and that 0.36 weight part of decylamine was used in lieu of 0.17 weight part

of decylamine. The results are shown in Table 11.

Comparative Example 19

- 5 **[0275]** A resin film was prepared and evaluated as in Example 42 except that 0.30 weight part of dodecylbenzenesulfonic acid was used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

Comparative Example 20

- 10 **[0276]** A resin film was prepared and evaluated as in Example 42 except that 0.50 weight part of sodium dodecylbenzenesulfonate was used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

- 15 Comparative Example 21

- 20 **[0277]** A resin film was prepared and evaluated as in Example 42 except that 0.50 weight part of dodecyltrimethylammonium chloride was used in lieu of 0.33 weight part of dodecylbenzenesulfonic acid and 0.17 weight part of decylamine. The results are shown in Table 11.

25

30

35

40

45

50

55

Table 11

	Sulfonic acid		Amine			Haze after 24 hours of immersion (%)
	kind	addition amount	R ³	R ⁶	R ⁷	
4 2	dodecylbenzenesulfonic acid	0. 3 3	decyl	H	H	18. 8
4 3	dodecylbenzenesulfonic acid	0. 1 7	decyl	H	H	12. 5
4 4	dodecylbenzenesulfonic acid	0. 0 3	decyl	H	H	17. 2
4 5	dodecylbenzenesulfonic acid	0. 3 3	octyl	methyl	methyl	10. 4
4 6	dodecylbenzenesulfonic acid	0. 1 7	octyl	methyl	methyl	11. 2
4 7	dodecylbenzenesulfonic acid	0. 0 3	octyl	methyl	methyl	13. 6
4 8	dodecylbenzenesulfonic acid	0. 3 0	dodecyl	methyl	methyl	16. 4
4 9	dodecylbenzenesulfonic acid	0. 1 2	dodecyl	methyl	methyl	17. 2
1 7	—	0	—	—	—	33. 4
1 8	—	0	decyl	H	H	59. 2
1 9	dodecylbenzenesulfonic acid	0. 3 0	—	—	—	resin degradation
2 0	Sodium dodecylbenzenesulfonate		0. 5 0			68. 4
2 1	Dodecyltrimethylammonium chloride		0. 5 0			54. 7

Example 50

[0278] One-hundred (100) weight parts of the poly(vinyl - butyral) resin synthesized in Example 32, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.30 weight part of octanoic acid and 0.35 weight part of decylamine were kneaded together and press-molded under the same conditions as in Example 32 to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing test as in Example 1. The results are shown in Table 12.

Example 51

[0279] A resin film was prepared and evaluated as in Example 50 except that 0.40 weight part of dodecylamine was used in lieu of 0.35 weight part of decylamine. The results are shown in Table 12.

Example 52

[0280] A resin film was prepared and evaluated as in Example 50 except that 0.45 weight part of tetradecylamine was used in lieu of 0.35 weight part of decylamine. The results are shown in Table 12.

Example 53

[0281] A resin film was prepared and evaluated as in Example 50 except that 0.50 weight part of myristic acid and 0.40 weight part of dodecylamine were used in lieu of 0.30 weight part of octanoic acid and 0.35 weight part of decylamine. The results are shown in Table 12.

Example 54

[0282] A resin film was prepared and evaluated as in Example 50 except that 0.45 weight part of N,N-dimethyldodecylamine was used in lieu of 0.35 weight part of decylamine. The results are shown in Table 12.

Example 55

[0283] A resin film was prepared and evaluated as in Example 50 except that 0.30 weight part of benzoic acid and 0.40 weight part of dodecylamine were used in lieu of 0.30 weight part of octanoic acid and 0.35 weight part of decylamine. The results are shown in Table 12.

Comparative Example 22

[0284] A resin film was prepared and evaluated as in Example 50 except that the addition of 0.35 weight part of decylamine was omitted. The results are shown in Table 12.

Table 12

	Carboxylic acid		Amine				Haze after 24 hours of immersion (%)
	kind	addition amount	R ^b	R ^c	R ^d	addition amount	
5 0	octanoic acid	0. 3 0	decyl	H	H	0. 3 5	23. 4
5 1	octanoic acid	0. 3 0	dodecyl	H	H	0. 4 0	24. 9
5 2	octanoic acid	0. 3 0	tetra-decyl	H	H	0. 4 5	23. 7
5 3	myristic acid	0. 5 0	dodecyl	H	H	0. 4 0	29. 6
5 4	octanoic acid	0. 3 0	dodecyl	methyl	methyl	0. 4 5	29. 6
5 5	benzoic acid	0. 3 0	dodecyl	H	H	0. 4 0	27. 0
2 2	octanoic acid	0. 3 0	—	—	—	0	75. 0
Compar. Example							

Example 56

[0285] One-hundred (100) weight parts of the poly(vinyl - butyral) resin prepared in Example 42, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine were kneaded together and press-molded under the same conditions as in Example 32 to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing resistance test as in Example 1. The results are shown in Table 13.

Example 57

[0286] A resin film was prepared and evaluated as in Example 56 except that 0.17 weight part of di(n-butyl)phosphoric acid and 0.13 weight part of N,N-dimethyloctylamine were used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Example 58

[0287] A resin film was prepared and evaluated as in Example 56 except that 0.19 weight part of di(n-ethylhexyl) phosphoric acid and 0.11 weight part of dodecylamine were used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Example 59

[0288] A resin film was prepared and evaluated as in Example 56 except that 0.20 weight part of di(n-ethylhexyl) phosphoric acid and 0.10 weight part of N,N-dimethyloctylamine were used in lieu of 0.16 weight part of di(n-butyl) phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Example 60

[0289] A resin film was prepared and evaluated as in Example 56 except that 0.20 weight part of di(n-dodecyl) phosphoric acid and 0.10 weight part of dodecylamine were used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Example 61

[0290] A resin film was prepared and evaluated as in Example 56 except that 0.21 weight part of di(2-dodecyl) phosphoric acid and 0.09 weight part of N,N-dimethyloctylamine were used in lieu of 0.16 weight part of di(n-butyl) phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Example 62

[0291] A resin film was prepared and evaluated as in Example 56 except that 0.17 weight part of diphenylphosphoric acid and 0.13 weight part of dodecylamine were used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Comparative Example 23

[0292] A resin film was prepared and evaluated as in Example 56 except that 0.30 weight part of sodium mono(n-dodecyl)phosphate was used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Comparative Example 24

[0293] A resin film was prepared and evaluated as in Example 56 except that 0.33 weight part of dodecyltrimethylammonium chloride was used in lieu of 0.16 weight part of di(n-butyl)phosphoric acid and 0.14 weight part of dodecylamine. The results are shown in Table 13.

Table 13

	Phosphoric acid				Aniline				Haze after 24 hours of immersion (%)	
	R ³	R ⁴	Addition amount	R ⁵	R ⁶	R ⁷	Addition amount			
Example	5 6	n-butyl	n-butyl	0. 1 6	dodecyl	H	H	0. 1 4	1 6. 5	
	5 7	n-butyl	n-butyl	0. 1 7	octyl	methyl	methyl	0. 1 3	1 7. 3	
	5 8	2-ethylhexyl	2-ethylhexyl	0. 1 9	dodecyl	H	H	0. 1 1	1 2. 6	
	5 9	2-ethylhexyl	2-ethylhexyl	0. 2 0	octyl	methyl	methyl	0. 1 0	1 4. 6	
	6 0	n-dodecyl	n-dodecyl	0. 2 0	dodecyl	H	H	0. 1 0	1 3. 4	
	6 1	n-dodecyl	n-dodecyl	0. 2 1	octyl	methyl	methyl	0. 0 9	1 5. 0	
	6 2	phenyl	phenyl	0. 1 7	dodecyl	H	H	0. 1 3	1 6. 7	
Compar. Example	2 3	Sodium (n-dodecyl)phosphoric acid							0. 3 0	5 7. 9
	2 4	Dodecyltrimethylammonium chloride							0. 3 3	5 4. 7

Example 63

(1) Preparation of a poly(vinyl acetal) resin

[0294] In 2890 g of pure water was dissolved 275 g of a poly(vinyl alcohol) having an average polymerization degree of 1700 and a saponification degree of 98.9 mole % under warming. After the temperature of the reaction system was adjusted to 12°C, 201 g of 35 weight % hydrochloric acid catalyst and 148 g of n-butyraldehyde were added and the mixture was incubated at the same temperature to precipitate the reaction product. The reaction system was then maintained at 45°C for 3 hours to carry the reaction to completion. The reaction mixture was washed with an excess

of water to remove the unreacted n-butyraldehyde and the catalyst hydrochloric acid was neutralized with aqueous sodium hydroxide solution. The mixture was further washed with an excess of water for 2 hours and then dried to provide a white powdery poly(vinyl butyral) resin. This poly(vinyl butyral) resin showed an average polymerization degree of 1700, a butyralization degree of 65 mole %, a residual acetyl group content of 1 mole %, a residual vinyl alcohol content of 34 mole %, a neutral salt (NaCl) content of 20 ppm as sodium, and a neutral salt particle diameter of 2 μm .

(2) Production of an interlayer film for laminated glass

[0295] To 100 parts of the poly(vinyl butyral) resin obtained as above were added 40 parts of the plasticizer triethylene glycol di-2-ethylbutyrate (3GH), 0.071 part (2.8×10^{-4} mole) of the metal salt of carboxylate (bond strength control agent) magnesium 2-ethylbutanoate (of 6 carbons) and suitable amounts of ultraviolet absorber and antioxidant, followed by thorough mixing. The organic acid content of the 3GH used above was 100 ppm. Then, using a compact extruder (trade name: Laboplastomill, Toyo Precision Machinery) equipped with a T-die, the mixture prepared as above was extruded at an extrusion temperature of 80 to 180°C and a die exit temperature of 200°C to provide an interlayer film for laminated glass of about 0.8 mm in thickness.

(3) Production of a laminated glass

[0296] After the interlayer film for laminated glass prepared as above was conditioned in a constant-temperature, constant humidity chamber to a water content of 0.4 to 0.5 weight %, it was sandwiched between two float glass sheets (2.4 mm thick) and prebonded by means of a roll. This prebonded assembly was post-bonded in an autoclave at a temperature of 130°C and a pressure of 13 kg/cm² to provide a laminated glass.

(4) Evaluation

[0297] The performance characteristic (Pummel value) of the above laminated glass was evaluated by the method described below. The moisture resistance of the laminate was evaluated by the method described in Example 1. The results are set forth in Table 14.

Evaluation method

(1) Pummel value

[0298] The laminated glass left standing at a temperature of $-18 \pm 0.6^\circ\text{C}$ for 16 hours for conditioning is stricken with a hammer having a head weighing 0.45 kg until the diameter of glass fragments produced has reached 6 mm or less. Then, the extent of exposure of the interlayer film after partial exfoliation of the glass was evaluated against the graded limit sample and converted to a Pummel value according to the criteria shown in Table 1. The Pummel value was determined under three conditions, (a) initial, (b) after 1 month at 50°C, and (c) after 2 months at 50°C. The larger the Pummel value is, the higher is the bond strength between sheet and glass. By the same token, the smaller the Pummel value is, the lower is the bond strength between the interlayer film and the glass.

Examples 64 to 69

[0299] Except that the metal salt of carboxylates shown in Table 14 were respectively used as the bond strength control agent, the procedure of Example 63 was otherwise repeated to provide interlayer film for laminated glasses and glass laminates.

Comparative Example 25

[0300] Except that 0.04 part (2.8×10^{-4} mole) of magnesium acetate (of 2 carbons) was used in lieu of 0.071 part of magnesium 2-ethylbutanoate as the metal salt of carboxylate in the preparation of an interlayer film for laminated glass, the procedure of Example 63 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

Comparative Example 26

[0301] Except that the metal salt of carboxylate shown in Table 14 was incorporated as the bond strength control

EP 1 022 261 B1

agent, the procedure of Example 63 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0302] The performance characteristics of the laminated glasses obtained in Examples 64 to 69 and Comparative Examples 25 and 26 were evaluated as in Example 63. The results are set forth in Table 14.

5

10

15

20

25

30

35

40

45

50

55

Table 14

	Plasticizer	Metal salt of carboxylate (the bond strength control agent)		Panner value			Haze after 24 hours of im- -rsion (%)
		kind	amount ($\times 10^{-4}$ mole)	Initial	Passed time A	Passed time B	
Example	6 3	3 GH (4 0)	magnesium 2-ethylbutanoate	0. 0 7 1 (2. 8)	5	5	4 1
	6 4	3 GH (4 0)	magnesium pentanoate	0. 0 6 3 (2. 8)	5	5	4 9
	6 5	3 GH (4 0)	zinc 2-ethylbutanoate	0. 0 8 9 (3. 0)	5	4	3 8
	6 6	3 GH (4 0)	potassium pentanoate	0. 0 4 5 (3. 2)	5	5	2 7
	6 7	3 GH (4 0)	magnesium 2-ethylpentanoate	0. 0 7 9 (2. 8)	5	3	3 8
	6 8	3 GH (4 0)	magnesium 2-ethylhexanoate	0. 0 8 7 (2. 8)	5	3	3 1
Compar. Example	6 9	3 GH (4 0)	magnesium decanoate	0. 1 0 3 (2. 8)	5	1	2 8
	2 5	3 GH (4 0)	magnesium acetate	0. 0 4 0 (2. 8)	5	5	9 2
	2 6	3 GH (4 0)	magnesium butanoate	0. 0 5 6 (2. 8)	5	5	9 0

Example 70

[0303] An interlayer film for laminated glass was prepared as in Example 63 except that the following composition was used: 100 parts of the poly(vinyl butyral) resin prepared as in Example 65 (average degree of polymerization: 1650, degree of butyralization: 67 mole %, residual acetyl group content: 1 mole %, residual vinyl alcohol content: 32 mole %, sodium content: 20 ppm, neutral salt particle diameter: 2 μm) as the poly(vinyl acetal) resin, 38 parts of triethylene glycol di-2-ethylhexanoate (3GO) as the plasticizer, 0.071 part (2.8×10^{-4} mole) of magnesium 2-ethylbutanoate (of 6 carbons) as the metal salt of carboxylate, suitable amounts of ultraviolet absorber and antioxidant.

[0304] Using the interlayer film for laminated glass obtained as above, a laminated glass was fabricated in the same manner as in Example 63.

Examples 71 and 72

[0305] Except that the metal salt of carboxylates shown in Table 15 were respectively used as the bond strength control agent, the procedure of Example 70 was otherwise repeated to provide interlayer film for laminated glasses and glass laminates.

Example 73

[0306] An interlayer film for laminated glass and a laminated glass were prepared as in Example 70 except that a poly(vinyl butyral) resin (average degree of polymerization: 1650, degree of butyralization: 67 mole %, residual acetyl group content: 1 mole %, residual vinyl alcohol content: 32 mole %), the neutral salt (sodium chloride) content of which had been reduced to 10 ppm as sodium by washing with pure water was used as the poly(vinyl acetal) resin.

Examples 74 to 78

[0307] Except that the metal salt of carboxylates shown in Table 15 were respectively used as the bond strength control agent, the procedure of Example 70 was otherwise repeated to provide interlayer film for laminated glasses and glass laminates.

Comparative Example 27

[0308] An interlayer film for laminated glass and a laminated glass were prepared as in Example 70 except that 0.04 part (2.8×10^{-4} mole) of magnesium acetate was added in lieu of 0.071 part of magnesium 2-ethylbutanoate as the metal salt of carboxylate in the preparation of an interlayer film for laminated glass.

[0309] The performance characteristics of the glass laminates obtained in Examples 70 to 78 and Comparative Example 27 were evaluated as in Example 63. The results are set forth in Table 15.

Table 15

	Plasticizer	Metal salt of carboxylate (the bond strength control agent)		Panmer value			Haze after 24 hours of im- mersion (%)
		Kind	amount ($\times 10^{-4}$ mole)	Initial	Passed time A	Passed time B	
70	3G0 (38)	magnesium 2-ethylbutanoate	0. 071 (2. 8)	5	5	5	42
71	3G0 (38)	magnesium octanoate	0. 087 (2. 8)	5	5	4	34
72	3G0 (38)	magnesium 2-ethylhexanoate potassium formate	0. 061 (2. 0) 0. 021 (2. 5)	5	4	4	38
73	3G0 (38)	magnesium 2-ethylbutanoate	0. 071 (2. 8)	5	5	5	21
74	3G0 (38)	magnesium 2-ethylpentanoate	0. 079 (2. 8)	5	3	2	37
75	3G0 (38)	magnesium 2-ethylhexanoate	0. 087 (2. 8)	5	3	1	33
76	3G0 (38)	magnesium nonanoate	0. 095 (2. 8)	5	2	1	29
77	3G0 (38)	magnesium decanoate	0. 103 (2. 8)	5	2	1	32
78	3G0 (38)	magnesium 2-ethylhexanoate potassium formate	0. 061 (2. 0) 0. 021 (2. 5)	5	3	2	39
Compar. Example	27	3G0 (38)	0. 040 (2. 8)	5	5	5	92

Example 79

[0310] An interlayer film for laminated glass was prepared by the same procedure as in Example 63 except that the following sheet composition was used: 100 parts of a poly(vinyl butyral) resin (average degree of polymerization: 1720, degree of butyralization: 66 mole %, residual acetyl group content: 1 mole %, residual vinyl alcohol content: 33 mole %, sodium content: 20 ppm, neutral salt particle diameter: 2 μm) as the poly(vinyl acetal) resin, 39 parts of tetraethylene glycol di-2-ethylhexanoate (4GO) as the plasticizer, 0.079 part (2.8×10^{-4} mole) of magnesium 2-ethylpentanoate (of 7 carbons) as the metal salt of carboxylate, and suitable amounts of ultraviolet absorber and antioxidant.

[0311] Using the interlayer film for laminated glass obtained as above, a laminated glass was fabricated as in Example 63.

Examples 80 to 82

[0312] Except that the metal salt of carboxylates shown in Table 16 were respectively used as the bond strength control agent, the procedure of Example 79 was otherwise repeated to provide interlayer film for laminated glasses and glass laminates.

Comparative Example 28

[0313] An interlayer film for laminated glass and a laminated glass were prepared as in Example 79 except that 0.04 part (2.8×10^{-4} mole) of magnesium acetate (of 2 carbons) was used in lieu of 0.079 part of magnesium 2-ethylpentanoate as the metal salt of carboxylate in the preparation of the interlayer film for laminated glass.

[0314] The performance characteristics of the glass laminates obtained in Examples 79 to 82 and Comparative Example 28 were evaluated as in Example 63. The results are set forth in Table 16.

Table 16

	Prastitizer	Metal salt of carboxylate (the bond strength control agent)		Panner value			Haze after 24 hours of im- -rsion (%)
		kind	amount ($\times 10^{-4}$ mole)	Initial	Passed time A	Passed time B	
Example	79 4 G 0 (39)	magnesium 2-ethylpentanoate	0. 0 7 9 (2. 8)	5	5	5	3 2
	80 4 G 0 (39)	magnesium 2-ethylbutanoate	0. 0 7 1 (2. 8)	5	3	2	4 0
	81 4 G 0 (39)	magnesium 2-ethylhexanoate	0. 0 8 7 (2. 8)	5	3	1	2 8
	82 4 G 0 (39)	magnesium nonanoate	0. 0 9 5 (2. 8)	5	3	2	2 5
Compar. Example	28 4 G 0 (39)	magnesium acetate	0. 0 4 0 (2. 8)	5	5	5	9 2

Example 83

[0315] An interlayer film for laminated glass was prepared as in Example 63 except that the following composition was used: 100 parts of a poly(vinyl butyral) resin (average degree of polymerization: degree of 1650, butyralization: 68 mole %, residual acetyl group content: 1 mole %, residual vinyl alcohol content: 31 mole %), the neutral salt (sodium chloride) content of which had been reduced to 20 ppm as sodium by washing with pure water, as the poly(vinyl acetal) resin, 36 parts of dihexyl adipate (DHA) as the plasticizer, 0.071 part (2.8×10^{-4} mole) of magnesium 2-ethylbutanoate (of 6 carbons) as the metal salt of carboxylate, and suitable amounts of ultraviolet absorber and antioxidant.

[0316] Using the laminate glass interlayer film obtained as above, a laminated glass was fabricated as in Example 63.

Examples 84 and 85

[0317] Except that the metal salt of carboxylates shown in Table 17 were respectively used as the bond strength control agent, interlayer film for laminated glasses and glass laminates were prepared as in Example 83.

Comparative Example 29

[0318] An interlayer film for laminated glass and a laminated glass were prepared as in Example 83 except that 0.04 part (2.8×10^{-4} mole) of magnesium acetate (of 2 carbons) was added in lieu of 0.071 part of magnesium 2-ethylbutanoate as the metal salt of carboxylate in the preparation of the interlayer film.

Comparative Example 30

[0319] Except that the metal salt of carboxylate shown in Table 17 was used as the bond strength control agent, the procedure of Example 83 was otherwise repeated to provide an interlayer film for laminated glass and a laminated glass.

[0320] The performance characteristics of the glass laminates obtained in Examples 83 to 85 and Comparative Examples 29 and 30 were evaluated as in Example 63. The results are set forth in Table 17.

Table 17

	Prastizier kind (amount)	Metal salt of carboxylate (the bond strength control agent)		Pammer value			Haze after 24 hours of immersion (%)
		Kind	Amount ($\times 10^{-4}$ mole)	Initial	Passed time A	Passed time B	
Example	83	DHA (36)	magnesium 2-ethylbutanoate	5	5	4	38
	84	DHA (36)	magnesium pentanoate	5	5	4	46
	85	DHA (36)	magnesium 2-ethylpentanoate	5	3	2	26
Compar. Example	29	DHA (36)	magnesium acetate	5	5	5	92
	30	DHA (36)	magnesium butanoate	5	5	5	84

Example 86

[0321] One-hundred (100) weight parts of the poly(vinyl butyral) resin obtained in Example 42, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine were kneaded together and press-molded under the same conditions as in Example 42 to provide a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing test as in Example 1. The results are shown in Table 18.

Example 87

[0322] A resin film was prepared and evaluated in the same manner as in Example 86 except that 0.043 weight part of hydroxypropanesulfonic acid and 0.057 weight part of N,N-dimethyloctylamine were used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Example 88

[0323] Except that 0.056 weight part of mesitylenesulfonic acid was used in lieu of 0.056 weight part of camphorsulfonic acid, a resin film was prepared and evaluated as in Example 86. The results are shown in Table 18.

Example 89

[0324] A resin film was prepared and evaluated as in Example 86 except that 0.08 weight part of dodecylbenzenesulfonic acid and 0.02 weight part of pyridine were used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Example 90

[0325] A resin film was prepared and evaluated as in Example 86 except that 0.061 weight part of dodecylbenzenesulfonic acid and 0.039 weight part of p-toluidine were used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Example 91

[0326] A resin film was prepared and evaluated as in Example 86 except that 0.048 weight part of 1,1-cyclohexanediadicetic acid and 0.104 weight part of dodecylamine were used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Example 92

[0327] A resin film was prepared and evaluated as in Example 86 except that 0.042 weight part of salicylic acid and 0.06 weight part of dodecylamine were used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Comparative Example 31

[0328] A resin film was prepared and evaluated as in Example 86 except that 0.1 weight part of pyridine was used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Comparative Example 32

[0329] A resin film was prepared and evaluated as in Example 86 except that 0.1 weight part of salicylic acid was used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Comparative Example 33

[0330] A resin film was prepared and evaluated as in Example 86 except that 0.1 weight part of sodium camphorsul-

EP 1 022 261 B1

fonate was used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

Comparative Example 34

5

[0331] A resin film was prepared and evaluated as in Example 86 except that 0.1 weight part of pyridinium chloride was used in lieu of 0.056 weight part of camphorsulfonic acid and 0.044 weight part of N,N-dimethyloctylamine. The results are shown in Table 18.

10

15

20

25

30

35

40

45

50

55

Table 18

	Organic acid		Amine		Haze after 24 hours of immersion (%)
	kind	addition amount	kind	addition amount	
86	camphorsulfonic acid	0.056	N,N-dimethyloctyl amine	0.044	25.7
87	hydroxypropanesulfonic acid	0.043	N,N-dimethyloctyl amine	0.057	29.0
88	mesylenesulfonic acid	0.056	N,N-dimethyloctyl amine	0.044	20.4
89	dodecylbenzenesulfonic acid	0.08	pyridine	0.02	21.4
90	dodecylbenzenesulfonic acid	0.061	p-toluidine	0.039	19.8
91	1,1-cyclohexane diacetate	0.048	dodecylamine	0.104	26.9
92	salicylic acid	0.042	dodecylamine	0.06	26.1
31	—	—	pyridine	0.1	46.2
32	salicylic acid	0.1	—	—	35.1
33	Sodium camphorsulfonate			0.1	66.2
34	pyridinium chloride			0.1	54.7

Example 93

[0332] One-hundred (100) weight parts of the poly(vinyl butyral) resin prepared in Example 42, 40 weight parts of triethylene glycol di-2-ethylbutyrate, 0.4 weight part of octanoic acid, 0.11 weight part of N,N-dimethyloctylamine and 0.037 weight part of magnesium 2-ethylbutyrate were kneaded together and press-molded as in Example 42 to provide

a resin film of 0.8 mm in thickness. This resin film was subjected to a moist blushing test as in Example 1.

[0333] In addition, the above resin film was sandwiched between two glass sheets (4x4 cm) to fabricate a laminated glass. Using this laminated glass, a peeling test was performed by the following method. The results are shown in Table 19.

Peeling test

[0334] The laminated glass was immersed in water at 60°C for 1 week and dried in an oven at 80°C for 4 hours. This immersion and drying cycle was repeated for a total of 3 times and the degree of exfoliation of the interlayer film adjoining to the laminated glass was visually examined.

Example 94

[0335] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the amount of N,N-dimethyloctylamine was altered to 0.28 weight part. The results are shown in Table 19.

Example 95

[0336] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the amount of octanoic acid was altered to 0.1 weight part and that of N,N-dimethyloctylamine was altered to 0.06 weight part. The results are shown in Table 19.

Example 96

[0337] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the amount of octanoic acid and N,N-dimethyloctylamine were altered to 0.2 weight part and 0.09 weight part, respectively, and, in addition, 0.045 weight part of magnesium 2-ethylhexanoate was used in lieu of 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Example 97

[0338] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the amount of octanoic acid and N,N-dimethyloctylamine were altered to 0.1 weight part and 0.06 weight part, respectively, and that 0.045 weight part of magnesium 2-ethylhexanoate was used in lieu of 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Example 98

[0339] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the amount of octanoic acid was altered to 0.1 weight part and that 0.06 weight part of decylamine and 0.045 weight part of magnesium 2-ethylhexanoate were used in lieu of 0.11 weight part of N,N-dimethyloctylamine and 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Example 99

[0340] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that 0.03 weight part of di(2-ethylhexyl)phosphoric acid was used in lieu of 0.4 weight part of octanoic acid and that the amount of N,N-dimethyloctylamine was altered to 0.02 weight part. The results are shown in Table 19.

Comparative Example 35

[0341] The laminated glass obtained in Comparative Example 12 was subjected to a peeling test as in Example 93. The results are shown in Table 19.

Comparative Example 36

[0342] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the addition of octanoic acid and N,N-dimethyloctylamine was omitted. The results are shown in Table 19.

Comparative Example 37

[0343] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the addition of N,N-dimethyloctylamine was omitted. The results are shown in Table 19.

Comparative Example 38

[0344] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the addition of octanoic acid was omitted. The results are shown in Table 19.

Comparative Example 39

[0345] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that the addition of octanoic acid and N,N-dimethyloctylamine was omitted and that 0.045 weight part of magnesium 2-ethylhexanoate was used in lieu of 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Comparative Example 40

[0346] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that 0.2 weight part of octanoic acid and 0.045 weight part of magnesium 2-ethylhexanoate were used in lieu of 0.4 weight part of octanoic acid, 0.11 weight part of N,N-dimethyloctylamine and 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Comparative Example 41

[0347] A resin film and a laminated glass were prepared and evaluated as in Example 93 except that 0.1 weight part of octanoic acid and 0.045 weight part of magnesium 2-ethylhexanoate were used in lieu of 0.4 weight part of octanoic acid, 0.11 weight part of N,N-dimethyloctylamine and 0.037 weight part of magnesium 2-ethylbutyrate. The results are shown in Table 19.

Table 19



	Organic acid		Amine		Organic acid magnesium		Haze after 24 hours of immersion (X)	Presence or absence of peeling
	kind	addition amount	kind	addition amount	kind	addition amount		
93	octanoic acid	0.4	N,N-dimethyloctylamine	0.11	magnesium 2-ethylbutyrate	0.037	24.3	none
94	octanoic acid	0.4	N,N-dimethyloctylamine	0.28	magnesium 2-ethylbutyrate	0.037	22.5	none
95	octanoic acid	0.1	N,N-dimethyloctylamine	0.06	magnesium 2-ethylbutyrate	0.037	25.3	none
96	octanoic acid	0.2	N,N-dimethyloctylamine	0.09	magnesium 2-ethylhexanoate	0.045	19.0	none
97	octanoic acid	0.1	N,N-dimethyloctylamine	0.06	magnesium 2-ethylhexanoate	0.045	20.6	none
98	octanoic acid	0.1	decylamine	0.06	magnesium 2-ethylhexanoate	0.045	19.4	none
99	di(2-ethylhexyl)phosphoric acid	0.03	N,N-dimethyloctylamine	0.02	magnesium 2-ethylbutyrate	0.037	25.6	none
35	—	—	—	—	—	—	33.4	presence
36	—	—	—	—	magnesium 2-ethylbutyrate	0.037	68.9	none
37	octanoic acid	0.4	—	—	magnesium 2-ethylbutyrate	0.037	36.6	none
38	—	—	N,N-dimethyloctylamine	0.11	magnesium 2-ethylbutyrate	0.037	71.2	none
39	—	—	—	—	magnesium 2-ethylhexanoate	0.045	45.2	none
40	octanoic acid	0.2	—	—	magnesium 2-ethylhexanoate	0.045	36.7	none
41	octanoic acid	0.1	—	—	magnesium 2-ethylhexanoate	0.045	38.9	none

INDUSTRIAL APPLICABILITY

[0348] Having the constitution described above, the present invention provides an interlayer film for laminated glass and a laminated glass, which are substantially free from blushing along the peripheral edge of the glass even in a highly humid environment and not compromised in transparency, weather resistance, bond strength and penetration resistance.

Claims


1. An interlayer film for laminated glass consisting essentially of a plasticized poly(vinyl acetal) resin and having the haze of not more than 50%, as measured by using an integrating turbidimeter manufactured by Tokyo Denshoku, when said interlayer film with a thickness of 0.3 to 0.8 mm is cut to 4 x 4 cm and immersed in deionized water at 23°C for 24 hours.
2. The interlayer film for laminated glass according to claim 1, wherein the particle diameter of the sodium salt in said interlayer film is not greater than 5 µm and the concentration of sodium in the interlayer film is not greater than 50 ppm.
3. The interlayer film for laminated glass according to claim 1 or 2, wherein the particle diameter of the potassium salt in the interlayer film is not greater than 5 µm and the concentration of potassium in the interlayer film is not greater than 100 ppm.
4. The interlayer film for laminated glass according to any one of claims 1 to 3, which comprises a compound capable of forming a complex with sodium and potassium salts.
5. The interlayer film for laminated glass according to any one of claims 1 to 4, which comprises at least one member selected from the group consisting of a sulfonic acid containing 2 to 21 carbon atoms, a carboxylic acid containing 2 to 20 carbon atoms, a phosphoric acid of the general formula (II) below, and an amine of the general formula (III) below :



wherein R³ represents an aliphatic hydrocarbon group containing 1 to 18 carbon atoms or an aromatic hydrocarbon group containing 1 to 18 carbon atoms, R⁴ represents a hydrogen atom, an aliphatic hydrocarbon group containing 1 to 18 carbon atoms or an aromatic hydrocarbon group containing 1 to 18 carbon atoms; and R⁵, R⁶ and R⁷ may be the same or different and each represents a hydrogen atom, an aliphatic hydrocarbon group containing 1 to 20 carbon atoms or an aromatic hydrocarbon group containing 1 to 20 carbon atoms.

6. The interlayer film for laminated glass according to claim 5, which comprises a sulfonic acid containing 2 to 21 carbon atoms in an amount of 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
7. The interlayer film for laminated glass according to claim 5, which comprises a carboxylic acid containing 2 to 20 carbon atoms, preferably 6 to 14 carbon atoms, in an amount of 0.01 to 3 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
8. The interlayer film for laminated glass according to claim 5, which comprises a phosphoric acid of general Formula II, in an amount of 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
9. The interlayer film for laminated glass according to claim 6, which comprises an amine of formula III, in an amount of 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.

10. The interlayer film for laminated glass according to claim 7, which comprises an amine of formula III, in an amount of 0.01 to 3 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
11. The interlayer film for laminated glass according to claim 8, which comprises an amine of formula III, in an amount of 0.01 to 2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
12. The interlayer film for laminated glass according to any one of claims 1 to 11, which further comprises at least one member selected from the group consisting of alkali metal salts and alkaline earth metal salts.
13. The interlayer film for laminated glass according to claim 12, wherein the alkali metal salt has a particle diameter of not greater than 3 μm and the alkaline earth metal salt has a particle diameter of not greater than 3 μm .
14. The interlayer film for laminated glass according to claim 12 or 13, wherein the alkali metal salt is an alkali metal salt of an organic acid containing 5 to 16 carbon atoms and the alkaline earth metal salt is an alkaline earth metal salt of an organic acid containing 5 to 16 carbon atoms.
15. The interlayer film for laminated glass according to claim 14, wherein said alkaline earth metal salt of organic acid is a magnesium salt of a carboxylic acid or dicarboxylic acid containing 6 to 10 carbon atoms.
16. The interlayer film for laminated glass according to claim 12 to 14, wherein said alkali metal salt or alkaline metal salts is present in an amount of 0.01 to 0.2 parts by weight per 100 parts by weight of the poly(vinyl acetal) resin.
17. The interlayer film for laminated glass according to any one of claims 1 to 16, wherein said poly(vinyl acetal) resin is produced by the process which comprises washing the synthesized poly(vinyl acetal) resin with water until a pH of 5 or above is attained, and drying it at a temperature of not higher than 60°C, without resort to neutralization procedure.
18. The interlayer film for laminated glass according to claim 17, wherein said washing is carried out with water at a temperature of not lower than 40°C.
19. The interlayer film for laminated glass according to any one of claims 1 to 16, wherein said poly(vinyl acetal) resin is produced by the process which comprises using, in synthesizing a poly(vinyl acetal) resin by reacting poly(vinyl alcohol) with an aldehyde in the presence of hydrochloric acid catalyst, an epoxide as both a reaction terminator and a hydrochloric acid eliminator.
20. The interlayer film for laminated glass according to claim 19, wherein said epoxide has the following general formula (I)



wherein R^1 and R^2 each represents a hydrogen atom or an alkyl group and n represents an integer of 0 to 3.

21. The interlayer film for laminated glass according to any one of claims 1 to 20, wherein the plasticizer is selected from organic ester type plasticizers and phosphorus type plasticizers.
22. The interlayer film for laminated glass according to claim 21, wherein the plasticizer is an organic ester type plasticizer selected from triethylene glycol di-2-ethylbutyrate, triethylene glycol di-2-ethylhexanoate, triethylene glycol dicaprylate, triethylene glycol di-n-octoate, triethylene glycol di-n-heptoate, tetraethylene glycol di-n-heptoate, dibutyl sebacate, dioctyl azelate, dibutylcarbitol adipate, ethylene glycol di-2-ethylenebutyrate, 1,3-propylene glycol di-2-ethylbutyrate, 1,4-propylene glycol di-2-ethylenebutyrate, 1,4-butylene glycol di-2-ethylbutyrate, 1,2-butylene glycol di-2-ethylenebutyrate, diethylene glycol di-2-ethylbutyrate, diethylene glycol di-2-ethylhexanoate, dipropylene glycol di-2-ethylbutyrate, triethylene glycol di-2-ethylpentoate, tetraethylene glycol di-2-ethylbutyrate and diethylene glycol dicaprylate.

23. The interlayer film for laminated glass according to claims 21 or 22, wherein the addition amount of said plasticizer is 20 to 70 parts by weight per 100 parts of the poly(vinyl acetal) resin.

24. A laminated glass comprising at least one pair of glass sheets and, as interposed therebetween, the interlayer film according to any one of claims 1 to 23.

Patentansprüche


1. Zwischenschicht-Folie für Verbundglas, das im wesentlichen aus einem Poly(vinylacetal)-Weichharz besteht und eine Trübung von nicht mehr als 50%, gemessen unter Verwendung eines von Tokyo Denshoku hergestellten integrierenden Trübungsmessers, aufweist, wenn die Zwischenschicht-Folie mit einer Dicke von 0,3 bis 0,8 mm auf 4 x 4 cm zugeschnitten und 24 Stunden lang in entionisiertes Wasser bei 23°C getaucht wird.

2. Zwischenschicht-Folie für Verbundglas nach Anspruch 1, wobei der Teilchendurchmesser des Natriumsalzes in der Zwischenschicht-Folie nicht mehr als 5 µm beträgt und die Konzentration an Natrium in der Zwischenschicht-Folie nicht mehr als 50 ppm beträgt.

3. Zwischenschicht-Folie für Verbundglas nach Anspruch 1 oder 2, wobei der Teilchendurchmesser des Kaliumsalzes in der Zwischenschicht-Folie nicht mehr als 5 µm beträgt und die Konzentration an Kalium in der Zwischenschicht-Folie nicht mehr als 100 ppm beträgt.

4. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 3, welche eine Verbindung umfaßt, die in der Lage ist, mit Natrium- und Kaliumsalzen einen Komplex zu bilden.

5. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 4, welche mindestens einen Vertreter umfaßt, der ausgewählt ist aus einer 2 bis 21 Kohlenstoffatome enthaltenden Sulfonsäure, einer 2 bis 20 Kohlenstoffatome enthaltenden Carbonsäure, einer Phosphorsäure der allgemeinen Formel (II) unten und einem Amin der allgemeinen Formel (III) unten:



wobei R³ einen 1 bis 18 Kohlenstoffatome enthaltenden aliphatischen Kohlenwasserstoffrest oder einen 1 bis 18 Kohlenstoffatome enthaltenden aromatischen Kohlenwasserstoffrest bedeutet, R⁴ ein Wasserstoffatom, einen 1 bis 18 Kohlenstoffatome enthaltenden aliphatischen Kohlenwasserstoffrest oder einen 1 bis 18 Kohlenstoffatome enthaltenden aromatischen Kohlenwasserstoffrest bedeutet; und R⁵, R⁶ und R⁷ gleich oder verschieden sein können und jeweils ein Wasserstoffatom, einen 1 bis 20 Kohlenstoffatome enthaltenden aliphatischen Kohlenwasserstoffrest oder einen 1 bis 20 Kohlenstoffatome enthaltenden aromatischen Kohlenwasserstoffrest bedeuten.


6. Zwischenschicht-Folie für Verbundglas nach Anspruch 5, welche eine 2 bis 21 Kohlenstoffatome enthaltende Sulfonsäure in einer Menge von 0,01 bis 2 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.

7. Zwischenschicht-Folie für Verbundglas nach Anspruch 5, welche eine 2 bis 20 Kohlenstoffatome, vorzugsweise 6 bis 14 Kohlenstoffatome, enthaltende Carbonsäure in einer Menge von 0,01 bis 3 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.

8. Zwischenschicht-Folie für Verbundglas nach Anspruch 5, welche eine Phosphorsäure der allgemeinen Formel II in einer Menge von 0,01 bis 2 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.

9. Zwischenschicht-Folie für Verbundglas nach Anspruch 6, welche ein Amin der Formel III in einer Menge von 0,01 bis 2 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.

10. Zwischenschicht-Folie für Verbundglas nach Anspruch 7, welche ein Amin der Formel III in einer Menge von 0,01 bis 3 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.
11. Zwischenschicht-Folie für Verbundglas nach Anspruch 8, welche ein Amin der Formel III in einer Menge von 0,01 bis 2 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes umfaßt.
12. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 11, welche weiter mindestens einen Vertreter umfaßt, der ausgewählt ist aus Alkalimetallsalzen und Erdalkalimetallsalzen.
13. Zwischenschicht-Folie für Verbundglas nach Anspruch 12, wobei das Alkalimetallsalz einen Teilchendurchmesser von nicht mehr als 3 µm aufweist und das Erdalkalimetallsalz einen Teilchendurchmesser von nicht mehr als 3 µm aufweist.
14. Zwischenschicht-Folie für Verbundglas nach Anspruch 12 oder 13, wobei das Alkalimetallsalz ein Alkalimetallsalz einer 5 bis 16 Kohlenstoffatome enthaltenden organischen Säure ist und das Erdalkalimetallsalz ein Erdalkalimetallsalz einer 5 bis 16 Kohlenstoffatome enthaltenden organischen Säure ist.
15. Zwischenschicht-Folie für Verbundglas nach Anspruch 14, wobei das Erdalkalimetallsalz einer organischen Säure ein Magnesiumsalz einer 6 bis 10 Kohlenstoffatome enthaltenden Carbonsäure oder Dicarbonsäure ist.
16. Zwischenschicht-Folie für Verbundglas nach Anspruch 12 bis 14, wobei das Alkalimetallsalz bzw. die Alkalimetallsalze in einer Menge von 0,01 bis 0,2 Gewichtsteilen pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes vorhanden ist bzw. sind.
17. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 16, wobei das Poly(vinylacetal)-Harz mit Hilfe des Verfahrens hergestellt wird, welches das Waschen des synthetisierten Poly(vinylacetal)-Harzes mit Wasser, bis ein pH von 5 oder darüber erreicht ist, und Trocknen desselben bei einer Temperatur von nicht mehr als 60°C, ohne auf ein Neutralisationsverfahren zurückzugreifen, umfaßt.
18. Zwischenschicht-Folie für Verbundglas nach Anspruch 17, wobei das Waschen mit Wasser bei einer Temperatur von nicht weniger als 40°C durchgeführt wird.
19. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 16, wobei das Poly(vinylacetal)-Harz mit Hilfe des Verfahrens hergestellt wird, das die Verwendung eines Epoxids sowohl als Reaktionsterminator als auch als Salzsäure-Abfänger bei der Synthese eines Poly(vinylacetal)-Harzes durch Umsetzen von Poly(vinylalkohol) mit einem Aldehyd in Gegenwart von Salzsäure-Katalysator umfaßt.
20. Zwischenschicht-Folie für Verbundglas nach Anspruch 19, wobei das Epoxid die folgende allgemeine Formel (I) aufweist



wobei R¹ und R² jeweils ein Wasserstoffatom oder einen Alkylrest bedeuten und n eine ganze Zahl von 0 bis 3 bedeutet.

- 21. Zwischenschicht-Folie für Verbundglas nach einem der Ansprüche 1 bis 20, wobei der Weichmacher ausgewählt ist aus Weichmachern vom organischen Ester-Typ und Weichmachern vom Phosphor-Typ.**
- 22. Zwischenschicht-Folie für Verbundglas nach Anspruch 21, wobei der Weichmacher ein Weichmacher vom organischen Ester-Typ ist, der ausgewählt ist aus Triethylenglykoldi-2-ethylbutyrat, Triethylenglykoldi-2-ethylhexanoat, Triethylenglykoldicaprylat, Triethylenglykoldi-n-octaat, Triethylenglykoldi-n-heptaat, Tetraethylenglykoldi-n-heptaat, Dibutylsebacat, Dioctylazelat, Dibutylcarbitoladipat, Ethylenglykoldi-2-ethylenbutyrat, 1,3-Propylenglykoldi-2-ethylbutyrat, 1,4-Propylenglykoldi-2-ethylenbutyrat, 1,4-Butylenglykoldi-2-ethylbutyrat, 1,2-Butylenglykoldi-**



2-éthylbutyrate, Diéthylenglykoldi-2-éthylbutyrate, Diéthylenglykoldi-2-éthylhexanoate, Dipropylenglykoldi-2-éthylbutyrate, Triéthylenglykoldi-2-éthylpentanoate, Tétraéthylenglykoldi-2-éthylbutyrate et Diéthylenglykoldicaprylate.

23. Zwischenschicht-Folie für Verbundglas nach den Ansprüchen 21 oder 22, wobei die Zugabemenge des Weichmachers 20 bis 70 Gewichtsteile pro 100 Gewichtsteile des Poly(vinylacetal)-Harzes beträgt.

24. Verbundglas, umfassend mindestens ein Paar Glasplatten und dazwischen die Zwischenschicht-Folie nach einem der Ansprüche 1 bis 23.

Revendications


1. Film intermédiaire pour verre feuilleté consistant essentiellement en une résine poly(vinylacétal) plastifiée et dont le trouble, mesuré à l'aide d'un turbidimètre intégrateur fabriqué par Tokyo Denshoku, est d'au plus 50 % lorsque ledit film intermédiaire ayant une épaisseur de 0,3 à 0,8 mm est découpé à 4 × 4 cm et immergé dans de l'eau désionisée à 23°C pendant 24 heures.
2. Film intermédiaire pour verre feuilleté selon la revendication 1, dans lequel le diamètre des particules de sels de sodium dans ledit film intermédiaire est d'au plus 5 µm et la concentration de sodium dans ledit film intermédiaire est d'au plus 50 ppm.
3. Film intermédiaire pour verre feuilleté selon la revendication 1 ou 2, dans lequel le diamètre des particules de sels de potassium dans ledit film intermédiaire est d'au plus 5 µm et la concentration de potassium dans ledit film intermédiaire est d'au plus 100 ppm.
4. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 3, qui comprend un composé capable de former un complexe avec les sels de sodium et de potassium.
5. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 4, qui comprend au moins un élément choisi dans le groupe constitué par un acide sulfonique contenant 2 à 21 atomes de carbone, un acide carboxylique contenant 2 à 20 atomes de carbone, un acide phosphorique de formule générale (II) ci-dessous, et une amine de formule générale (III) ci-dessous:



où R³ représente un groupe hydrocarboné aliphatique contenant 1 à 18 atomes de carbone ou un groupe hydrocarboné aromatique contenant 1 à 18 atomes de carbone, R⁴ représente un atome d'hydrogène, un groupe hydrocarboné aliphatique contenant 1 à 18 atomes de carbone ou un groupe hydrocarboné aromatique contenant 1 à 18 atomes de carbone, et R⁵, R⁶ et R⁷ peuvent être identiques ou différents et représentent chacun un atome d'hydrogène, un groupe hydrocarboné aliphatique contenant 1 à 20 atomes de carbone ou un groupe hydrocarboné aromatique contenant 1 à 20 atomes de carbone.

6. Film intermédiaire pour verre feuilleté selon la revendication 5, qui comprend un acide sulfonique contenant 2 à 21 atomes de carbone en une quantité de 0,01 à 2 parties en masse pour 100 parties en masse de résine poly(vinylacétal).
7. Film intermédiaire pour verre feuilleté selon la revendication 5, qui comprend un acide carboxylique contenant 2 à 20 atomes de carbone, de préférence 6 à 14 atomes de carbone, en une quantité de 0,01 à 3 parties en masse pour 100 parties en masse de la résine poly(vinylacétal).
8. Film intermédiaire pour verre feuilleté selon la revendication 5, qui comprend un acide phosphorique de formule générale II, en une quantité de 0,01 à 2 parties en masse pour 100 parties en masse de la résine poly(vinylacétal).

9. Film intermédiaire pour verre feuilleté selon la revendication 6, qui comprend une amine de formule III en une quantité de 0,01 à 2 parties en masse pour 100 parties en masse de la résine poly(vinylacétal).
10. Film intermédiaire pour verre feuilleté selon la revendication 7, qui comprend une amine de formule III en une quantité de 0,01 à 3 parties en masse pour 100 parties en masse de la résine poly(vinylacétal).
11. Film intermédiaire pour verre feuilleté selon la revendication 8, qui comprend une amine de formule III en une quantité de 0,01 à 2 parties en masse pour 100 parties en masse de la résine poly(vinylacétal).
12. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 11, qui comprend en outre au moins un élément choisi dans le groupe constitué par des sels de métaux alcalins et des sels de métaux alcalino-terreux.
13. Film intermédiaire pour verre feuilleté selon la revendication 12, dans lequel le sel de métal alcalin a un diamètre de particules d'au plus 3 μm et le sel de métal alcalino-terreux a un diamètre de particules d'au plus 3 μm .
14. Film intermédiaire pour verre feuilleté selon la revendication 12 ou 13, dans lequel le sel de métal alcalin est un sel de métal alcalin d'un acide organique contenant 5 à 16 atomes de carbone et le sel de métal alcalino-terreux est un sel de métal alcalino-terreux d'un acide organique contenant 5 à 16 atomes de carbone.
15. Film intermédiaire pour verre feuilleté selon la revendication 14, dans lequel ledit sel de métal alcalino-terreux d'acide organique est un sel de magnésium d'un acide carboxylique ou d'un acide dicarboxylique contenant 6 à 10 atomes de carbone.
16. Film intermédiaire pour verre feuilleté selon les revendications 12 à 14, dans lequel ledit sel de métal alcalin ou lesdits sels de métaux alcalins sont présents en une quantité de 0,01 à 0,2 partie en masse pour 100 parties en masse de la résine poly(vinylacétal).
17. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 16, dans lequel ladite résine poly(vinylacétal) est produite par un procédé qui comprend le lavage de la résine poly(vinylacétal) synthétisée avec de l'eau jusqu'à l'obtention d'un pH d'au moins 5, et son séchage à une température d'au plus 60°C, sans recours à une technique de neutralisation.
18. Film intermédiaire pour verre feuilleté selon la revendication 17, dans lequel ledit lavage s'effectue avec de l'eau à une température d'au moins 40°C.
19. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 16, dans lequel ladite résine poly(vinylacétal) est produite par un procédé comprenant l'utilisation, dans la synthèse de la résine poly(vinylacétal) par réaction de poly(alcool vinylique) avec un aldéhyde en présence d'acide chlorhydrique comme catalyseur, d'un époxyde à la fois comme agent de terminaison de la réaction et comme agent d'élimination de l'acide chlorhydrique.
20. Film intermédiaire pour verre feuilleté selon la revendication 19, dans lequel ledit époxyde a la formule générale (I) suivante



dans laquelle R^1 et R^2 représentent chacun un atome d'hydrogène ou un groupe alkyle et n représente un entier de 0 à 3.

21. Film intermédiaire pour verre feuilleté selon l'une quelconque des revendications 1 à 20, dans lequel le plastifiant est choisi parmi des plastifiants de type ester organique et des plastifiants de type phosphore.
22. Film intermédiaire pour verre feuilleté selon la revendication 21, dans lequel le plastifiant est un plastifiant de type

ester organique choisi parmi le di-2-éthylbutyrate de triéthylèneglycol, le di-2-éthylhexanoate de triéthylèneglycol, le dicaprylate de triéthylèneglycol, le di-n-octanoate de triéthylèneglycol, le di-n-heptanoate de triéthylèneglycol, le di-n-heptanoate de tétraéthylèneglycol, le sébacate de dibutyle, l'azélate de dioctyle, l'adipate de dibutylcarbitol, le di-2-éthylènebutyrate d'éthylèneglycol, le di-2-éthylbutyrate de 1,3-propylèneglycol, le di-2-éthylènebutyrate de 1,4-propylèneglycol, le di-2-éthylbutyrate de 1,4-butylèneglycol, le di-2-éthylènebutyrate de 1,2-butylèneglycol, le di-2-éthylbutyrate de diéthylèneglycol, le di-2-éthylhexanoate de diéthylèneglycol, le di-2-éthylbutyrate de dipropylèneglycol, le di-2-éthylpentanoate de triéthylèneglycol, le di-2-éthylbutyrate de tétraéthylèneglycol et le dicaprylate de diéthylèneglycol.

23. Film intermédiaire pour verre feuilleté selon les revendications 21 ou 22, dans lequel la quantité ajoutée dudit plastifiant est de 20 à 70 parties en masse pour 100 parties de la résine poly(vinylacétal).

24. Verre feuilleté comprenant au moins une paire de feuilles de verre et, placé entre elles, un film intermédiaire selon l'une quelconque des revendications 1 à 23.